Blasi, G., De Luca, F., Perrone, D., Greco, A., & Aiello, M. A. (2021). MID 1.1: Database for Characterization of the Lateral Behavior of Infilled Frames. *ASCE Journal of Structural Engineering*, 147(10), [04721007]. [https://doi.org/10.1061/\(ASCE\)ST.1943-541X.0003117](https://doi.org/10.1061/(ASCE)ST.1943-541X.0003117)

Peer reviewed version

Link to published version (if available):
[10.1061/\(ASCE\)ST.1943-541X.0003117](https://doi.org/10.1061/(ASCE)ST.1943-541X.0003117)

[Link to publication record in Explore Bristol Research](#)
PDF-document

This is the author accepted manuscript (AAM). The final published version (version of record) is available online via American Society of Civil Engineers at [https://doi.org/10.1061/\(ASCE\)ST.1943-541X.0003117](https://doi.org/10.1061/(ASCE)ST.1943-541X.0003117) . Please refer to any applicable terms of use of the publisher.

University of Bristol - Explore Bristol Research

General rights

This document is made available in accordance with publisher policies. Please cite only the published version using the reference above. Full terms of use are available:
<http://www.bristol.ac.uk/red/research-policy/pure/user-guides/ebr-terms/>

MID 1.1: Database for the characterization of the lateral behaviour of infilled frames

Gianni Blasi¹, Flavia De Luca², Daniele Perrone^{3,4}, Antonella Greco⁵, Maria Antonietta Aiello⁶

Abstract: The research on infilled reinforced concrete frames is fundamental for the vulnerability assessment of existing buildings. The analysis of the interaction between infill and frame is an open issue in performance-based earthquake engineering, due to its importance in predicting the dynamic behaviour and failure modes of buildings. This study provides an open access database of laboratory tests on masonry infilled reinforced concrete frames, collected from the literature and harmonized in a consistent framework. The data were grouped in categories, to calibrate a piecewise linear curve representing the lateral response of the infill, depending on the masonry wall and the frame details. The gathered data are used to assess analytical models and numerical studies from the literature, with the aim to revise the formulations currently used in the equivalent strut approach. An empirical model for the equivalent strut was developed, through a power-law multiple regression of the database. The open access database in its spreadsheet form is aimed at providing a useful tool for the analysis of infilled reinforced concrete frames.

(<https://doi.org/10.5523/bris.71oex4uyxye925b8fai0v1qk5>).

Author Keywords: reinforced concrete, infilled frames, laboratory test, database, empirical model.

1 INTRODUCTION

The importance of masonry infill walls in the seismic performance assessment of reinforced concrete (RC) buildings has been evidenced in past research. Several post-earthquake damage reports allowed to study the role of infill walls in the global behaviour of RC frames (Çelebi et al. 2010; Decanini et al. 2004; Fiore et al. 2012; De Luca et al. 2017; Manfredi et al. 2014; Sezen et al. 2003; Di Trapani et al. 2020; Verderame et al. 2011), even though this aspect is generally neglected in practical design.

The presence of the infill walls influences the seismic demand and the capacity of the structure, at both global and local level. Higher lateral strength and stiffness of infilled RC frames with respect to a “bare” configuration (namely with no infill walls) lead to major changes in the dynamic behaviour and the reduction of the fundamental period generally increases spectral accelerations (e.g. Dolšek and Fajfar 2008; Perrone et al. 2016). Consequently, although the infill walls enhance the strength capacity of the frame, the increase of the global seismic demand may lead to unconservative results

¹ Post-Doctoral Researcher, Department of Engineering for Innovation, University of Salento, Via per Monteroni, Lecce, Italy. E-mail: gianni.blasi@unisalento.it.

² Senior Lecturer, Department of Civil Engineering, University of Bristol, University Walk, Bristol BS8 1TR, UK.

³ Post-Doctoral Researcher, Department of Engineering for Innovation, Via per Monteroni, Lecce, University of Salento, Italy.

⁴ Post-Doctoral Researcher, University School for Advanced Studies IUSS Pavia, Piazza della Vittoria n.15, Pavia, Italy.

⁵ Graduate Student, Department of Engineering for Innovation, University of Salento, Via per Monteroni, Lecce, Italy.

⁶ Full Professor, Department of Engineering for Innovation, University of Salento, Via per Monteroni, Lecce, Italy.

when analysing the performance of strong infill-weak frame systems. Particularly, early brittle failure of columns with poor shear reinforcement can be caused by the interaction with the infill, reducing the displacement and energy dissipation capacity of the structure.

The correlation between failure modes of the frame and infill walls' properties was evidenced in past studies (Blasi et al. 2018b, 2020; Mehrabi et al. 1996; Pujol and Fick 2010), particularly in the case of existing buildings realized before the introduction of capacity design provisions in modern codes (pre-code buildings in the following) (e.g. Dolšek and Fajfar 2005; De Luca et al. 2014; Perrone et al. 2017). Post-earthquake damage observations and numerical simulations showed brittle failure of gravity load-designed frames caused by the increase of internal forces transferred from the infill to the columns (e.g. Blasi 2019; Ricci et al. 2011; Verderame et al. 2014). Recent building codes and standards (ASCE/SEI 41-17 2017; EN 1998-1 2005; FEMA 356 2000) address the issue of the RC frame-infill interaction by introducing provisions for the additional shear demand in the columns, depending on the lateral strength of the masonry panel.

The RC frame-infill interaction has been widely analysed in recent studies, with the aim of providing suitable numerical or analytical models for the accurate prediction of internal forces in the frame (Cavaleri and Di Trapani 2015; Milanesi et al. 2018; Pantò et al. 2017). The equivalent strut macro-model (Polyakov 1960) is still widely used and various configurations are available in the literature, depending on the number of trusses adopted and their mechanical properties (Chrysostomou et al. 2002; Crisafulli et al. 2005; Varum et al. 2005). The lateral force-displacement (F-d) behaviour of the equivalent strut and its cross-section are generally derived accounting for the properties of both the frame members and masonry infill walls (Bazan and Meli 1980; Liao and Kwan 1984; Mainstone 1971; Stafford Smith and Carter 1969).

Recent studies evidenced the main shortcomings of the most used formulations for the lateral response of infilled frames, which might fail in predicting the actual collapse mechanism of the frame (Blasi et al. 2018a) or neglect the failure mode of the infill wall in defining its lateral strength (Di Trapani et al. 2018). The development of data-driven approaches based on experimental results is a useful mean to identify the parameters influencing the behaviour of infilled frames and to improve analytical formulations for employment in the engineering practice. A comprehensive analysis of the lateral behaviour of infill walls was conducted by Huang et al. (Huang et al. 2020), by collecting a database of laboratory tests on masonry infilled RC frames. The data were used for multivariate regression analyses, to calibrate empirical formulations for the lateral response of the masonry infill.

This study is aimed at collecting a database of laboratory tests on infilled RC frames, to statistically define the main parameters ruling the lateral behaviour of the masonry wall. An expanded and openly available version of the Masonry Infilled Database, MID 1.0, (De Luca et al. 2016) is developed, considering a wider number of tests to investigate additional statistical and mechanical parameters. The database is called MID 1.1 and includes 134 quasi-static tests on masonry infilled RC portal frames, whose results are analysed in terms of Base-shear-displacement curves.

58 A piecewise linear approximation of the curves is derived for each test, to calibrate the parameters of a force-displacement
59 model for the infill wall, depending on masonry type and frame properties. The piecewise approximation allows the
60 consideration of additional metadata in MID 1.1, obtaining the monotonic curve of the infill-alone. Furthermore, the ratio
61 between the cracking strength and the maximum strength of the infill wall, as well as its elastic and post-peak softening
62 stiffness are investigated.

63 The characterization of the load-displacement shape of infilled RC frames, can be useful for seismic assessment methods
64 employing spectrum-based pushover approaches, which include the contribution of the infill walls in the global curve. To
65 this scope, the piecewise curves obtained from the database are compared to numerical pushover curves available in the
66 literature and to analytical models employed in equivalent strut approaches. Lastly, an empirical expression for the
67 definition of the equivalent strut width is derived from the database results, to be used in simplified analyses of infilled
68 RC frames.

69 The main innovation of the proposed database with respect to similar studies (Huang et al. 2020; Liberatore et al. 2018;
70 De Risi et al. 2018; Šipoš et al. 2013) is the detailed classification of the specimens, depending on both frame and infill
71 properties, the inclusion of additional infill types besides clay hollow bricks and open availability of the data in a usable
72 spreadsheet format.

73 The results of this work can be useful to improve code-oriented formulations for practical design. Additionally, specific
74 design criteria for infilled RC frames, accounting for different properties of the infill walls, can be used for the design of
75 new buildings. The MID 1.1 is available online as an open access file, which can be continuously updated. Several tools
76 to examine and group the data, depending on the parameters considered in this study, are available in the spreadsheet
77 format.

78 **2 MASONRY INFILL DATABASE MID 1.1**

79 The data are collected in an open access file (De Luca et al. 2020), which includes sections reporting the properties of the
80 specimens and the results of the tests. In addition to the tests data, several features to group and to statistically analyse the
81 results depending on user-defined parameters are included.

82 The Masonry Infilled Database 1.1 (MID 1.1) was developed by improving the existing MID 1.0 provided by De Luca et
83 al. (2016). The original version of the database mainly includes tests on RC portal frames with clay brick infill walls.
84 Therefore, one of the objectives of MID 1.1 is the inclusion of additional brick types of the infill, such as Aerated
85 Autoclaved Concrete (AAC), calcarenite, vitrified ceramic and fly ash bricks. These brick types are indeed increasingly
86 adopted in infill walls, due to their lower thermal transmittance and weight with respect to traditional clay or natural stone
87 bricks.

The main improvement in the MID 1.1 is the classification of the collected tests as function of the frame details (i.e. seismic details, number of floors) and the infill configuration (i.e. brick type, and void ratio of the wall). Different tests types were considered, such as pseudo-static monotonic or cyclic loading and pseudo-dynamic tests. Referring to the specimens, most of the collected data concern single-bay single-storey RC portal frame, with solid infill, whose dimension was mainly full-scaled, half-scaled and one-third-scaled.

The MID1.1 includes data sourced from 24 references, reported in **Table 1**. A total number of 134 tests are collected. The wider variety of infill types in MID 1.1 with respect to MID 1.0 and to most of the databases available in the literature (Liberatore et al. 2018; De Risi et al. 2018; Šipoš et al. 2013) allows a classification of the tests, based on several parameters. Particularly, the infill's brick type is classified as **CB**: clay bricks, **CON**: concrete, **AAC**: autoclaved aerated concrete and **Other**: calcarenite, vitrified ceramic and fly ash.

A comparison between MID 1.1 and MID 1.0 in terms of number of tests in each category is reported in **Figure 1a**. Despite both versions of the database include the same number of tests on infilled frames with clay brick walls (66), additional tests were collected in MID 1.1 for the remaining categories. Particularly, a specific characterization of **AAC** infill walls is allowed, due to the wider number of tests included in MID 1.1.

A comparison of the RC frame details is also provided (**Figure 1b**). The frames are classified as **SD** or **nSD** (i.e. Seismic Design or no Seismic Design), depending on longitudinal and transverse reinforcement indexes in beams and columns and on the relative beam-to-column resisting moment. Since the experimental campaigns refer to different seismic codes or standards, in the following context “seismic design” should be intended as implementation of seismic detailing according to a code or standard based on capacity design principles. In most cases, this classification reflects a compliance with provisions of Eurocode 8 (EN 1998-1 2005).

2.1 Data sources and classification

The database MID1.1 is composed of different sections, including all the features of the specimens collected. In Section 1: **SPECIMEN**, details on the geometry of the infilled portal frames are reported, namely number of bays, number of storeys, openings' geometry, type of loading protocol and test scale. As shown in **Figure 2**, most of the collected specimens are single-storey single-bay frames (93%); 11% are two-storey frames, while 7% and 1% are two bays and three bays, respectively. The infill-frame interface was realized using traditional mortar joints for most of the specimens and none of the portal frames featured gap between frame and infill. Haris and Farkas (2018) adopted steel plates embedded in RC members for 12 specimens, while dowel rebars were used for one specimen in (Al-Nimry 2014).

Section 2: **PANEL**, provides a classification of the infill walls, based on the properties of bricks and mortar joints, such as the presence and the direction of holes in bricks, the brick material, the mortar joints thickness and compressive strength of mortar. **Figure 3a** reports the distribution for infill's opening type. The specimens are classified as **BARE**, **SOL**, **WIN**

or **DOOR**, namely bare frames, infilled frames with solid infill, infilled frames with window opening and infilled frames with door opening, respectively. Most of the collected tests are referred to infilled frames with solid infill (78%), while 7.5% and 3.7% are infilled with window and door opening respectively.

In **Figure 3b**, the density distribution of the test scale is reported. Most of test are 1/2 or 1/3 scaled specimens (72%), while full-scaled tests represent only 20% of the data. This parameter could be useful to assess if the results collected might be affected by scale effects.

The details on the protocol employed in the collected tests for vertical and lateral loading are provided in **Figure 4a** and **4b**, respectively. For most for the cases, vertical load was directly applied on top of the column and kept constant (**CO**) during the tests. In fewer tests, vertical load was applied to either beams and columns or only beams, while only lateral load was applied in 14 cases. In one case, the detail on the vertical loading protocol are not available in the reference (na). Pseudo-static protocols have been mainly adopted for lateral loading, as shown in **Figure 4b**. The lateral load was applied through cyclic pseudo-static protocol (**C**) in 75% of the tests, while 14% and 11% are monotonic (**M**) pseudo-static or pseudo-dynamic (**P**), respectively.

In **Figure 5**, the density distributions of the aspect ratio, H_w/L_w (H_w = wall height, L_w = wall length), and of the slenderness, t_w/H_w , of the infill wall are provided. The aspect ratio ranges between 0.5 and 0.7 for 56% of the cases, while the minimum and the maximum value are equal to 0.48 and 1.0, respectively. The values collected in the database are consistent with the geometric configuration of the infill walls in typical residential buildings. Infilled RC frames are indeed mostly adopted in residential buildings, where the bay length and the inter-storey height generally range between 3.5 and 7.0 m and between 2.7 m and 4.5 m, respectively (e.g. Polese et al. 2008; Rossetto and Elnashai 2005).

The wall slenderness ratio is within 5.0 and 20.0 for most of the specimens, while the maximum and the minimum value are 4.3 and 40.0, respectively. It is worth evidencing that the wall thickness was not available (na) in the reference for 3.4% of the cases.

One of the main features of the database is the classification of the infill walls based on the brick units. In **Figure 6a** and **6b**, the density distribution of the brick material and the brick type is provided. The brick material is classified as reported in **Figure 1a**, considering four categories, while the brick type is defined based on the presence of holes (**HOLLOW** or **SOLID**).

In Mediterranean regions, manufactured bricks are mainly used for structural walls in low-rise masonry buildings and for non-structural applications (infill walls) in RC framed structures. For this reason, hollow clay or concrete units are generally preferred to solid bricks, because of their low weight and thermal conductivity. Solid clay bricks are typically adopted in northern Europe and in United States, where RC framed building are not as common as in Mediterranean regions. On the other hand, solid concrete bricks are widely used in South Asia (Basha and Kaushik 2016; Ganz 2003; De Luca et al. 2019; Salmanpour et al. 2012). **Figure 7** reports the number of specimens with hollow and solid units, in

case of concrete and clay bricks. The increasingly attention of the research community to the environment, has encouraged the adoption of novel materials, particularly in construction industry. The use of highly thermally insulating and sustainable materials (AAC, fly ash) in infill walls guarantees a significant reduction of the energy consumption in buildings (Al-Naghi et al. 2020). Considering its spreading, the *AAC* category was included in the MID 1.1, aiming to provide useful data for the definition of analytical models.

Referring to the mechanical properties of the bricks, a great variability of the data is observed. The compressive strength ranges between 1.79 and 26.2 MPa, with average equal to 8.47 MPa and coefficient of variation equal to 0.77. Concrete bricks feature significantly higher values (average equal to 13.85 MPa) compared to *CB*, *AAC* and *Other*, whose average compressive strength was equal to 6.66 MPa, 3.46 MPa and 5.53 MPa, respectively.

The details on the configuration of the RC frames are reported in Section 3: *FRAME*, including the dimension of the cross sections of the frame members and the mechanical properties of the concrete and the reinforcement steel. In Section 4: *REINFORCEMENT*, details on longitudinal and transverse reinforcement are provided. The data collected include concrete cover, diameter and number of reinforcement bars and reinforcement index. The information on the reinforcement allows for the specification of the presence of seismic design details in the RC frame.

The density distribution of the reinforcement index for longitudinal and transverse bars in columns are reported in **Figure 8**. According to the main building design codes (ACI 318-14 2014; EN 1992-1-1 2004), the longitudinal reinforcement index in columns ($\rho_{l,col}$) should range between 1% and 8%, while the range of transverse reinforcement index ($\rho_{t,col}$) is not explicitly defined. On the other hand, it is worth assuming a lower limit of $\rho_{t,col}$ equal to 0.4%, based on specific seismic codes provisions on the ductility capacity (EN 1998-1 2005) and on the mechanical properties of concrete and steel, usually adopted for constructions. For most of the collected tests, the longitudinal and transverse reinforcement indexes range between 1% and 3.5% and between 0.5% and 1.5% (**Figure 8**).

Section 5 provides a description of the failure modes (FMs) recorded in the tests, which are classified according to FEMA 306 (1998). Five different categories were defined, namely *A*, *B*, *C*, *D* and *E*, referred to corner crushing, diagonal cracking, sub-panel diagonal cracking, bed joint sliding and RC frame failure, respectively (**Figure 9**).

2.2 Damage state threshold distribution

The correlation between the damage on the infill and the lateral drift of the portal frame, is analysed based on the collected data. The lateral response of the specimens in the database was divided considering two Damage States (DS), namely *DS2* and *DS3*, as suggested in EMS-98 (1998). The *DS2* features medium-high damage to the infill, characterized by minor cracking, brittle cladding/plaster falls and mortar joints cracking. The *DS3* is characterized by major damage or collapse of the infill, featuring severe cracking paths and collapse of bricks, which cause complete loss of strength of the wall.

182 The collected data on the failure modes of the infill walls were organized by recording the drift at which **DS2** and **DS3**
 183 were achieved. The density distribution of the data along with the lognormal distribution fit is reported in **Figure 10a** and
 184 **b**, for **DS2** and **DS3**, respectively, displaying the median, η , and the logarithmic standard deviation, σ_{log} .
 185 The **DS2** attainment was not explicitly discussed in some of the collected tests, which mainly focused the ultimate limit
 186 state of the analysed portal frames. For most of the available data, the **DS2** corresponded to a drift ranging between 0.1-
 187 0.4%, with maximum value equal to 1.2%. Referring to **DS3**, the corresponding drift ranged between 0.3 and 2.5%, while
 188 the maximum value recorded was equal to 5%. The high values of σ evidence the uncertainty in the failure mode
 189 prediction, due to the influence of several parameters, as relative infill-to-frame stiffness and mechanical properties of
 190 bricks and mortar joints. The results obtained are consistent to the observations provided from recent studies focused on
 191 the damage assessment of RC buildings with hollow clay infill walls (Ricci et al. 2016; De Risi et al. 2018).
 192 It is worth mentioning that several references did not explicitly address the attainment of a specific damage state, hindering
 193 a reliable comparison between solid infilled frames and infilled frames with openings. Additionally, a similar variability
 194 is obtained grouping the data depending on the brick type. On the other hand, being this study aimed at characterizing the
 195 shape of the load-displacement behaviour of infilled frames regardless of the failure modes, these details are not required
 196 in the following.

197 **2.3 Piecewise linear fit of lateral backbones curves**

198 The force-displacement envelope curves obtained in the collected tests were approximated through a piece-wise linear
 199 fitting. The approximation procedure was developed by De Luca et al. (2013) and it is aimed at deriving, from the original
 200 curve, a multilinear behaviour, composed of four branches. A linear fit example is reported in (**Figure 11**). The grey and
 201 black solid lines are referred to the multi-linearization and the original curve, respectively.

202 The first stage of the curve represents the elastic response of the system, up to the attainment of the cracking strength of
 203 the infill, F_{cr} . The second post-cracking slope represents the generation of the strut mechanism in the wall, when lateral
 204 stiffness reduces due to the development of cracks in the infill. The post-cracking slope ends at the attainment of the peak
 205 strength, F_m , which is followed by two softening slopes, representing the degradation due to progressive increase of
 206 damage in the infill. Since the backbone curve is calibrated based on both monotonic and cyclic tests, the softening slopes
 207 refer to both in-cycle and cyclic degradation. Therefore, the piecewise model obtained is suitable for indirect modelling
 208 of the cyclic behaviour of infilled RC frames, according to NIST GCR 10-917-5 (Deierlein et al. 2010).

209 In the Section *Piecewise linear fit* of MID1.1, the load-displacement coordinates defining the multi-linear fit of each
 210 experimental curve are provided. The second softening slope is not included within the piecewise curves' data in the
 211 database, since K_{soft2} was either slightly lower than K_{soft1} or close to zero for most of the considered tests. For this reason,

three-linear curves featuring elastic, post-cracking and softening stiffness equal to K_1 , K_2 and K_{soft} , respectively, are provided in the database.

It is worth mentioning that the cyclic response of infilled RC frames may be significantly uneven in positive and negative direction, therefore the 134 curves fitted correspond to the average response in case of cyclic tests.

The force and displacement values in the obtained multi-linear curves are normalized to the peak strength, F_m , and to the corresponding displacement, D_m , respectively, aiming to obtain non-dimensional parameters ruling the shape of each curve. One of the objectives of this study is the estimation of the ratio between the maximum strength, F_m , and the cracking strength, F_{cr} , (overstrength ratio), whose values could be directly compared through the normalization described above.

In the section *Piecewise_Global* of the database, all the normalized curves are reported. The tests were grouped in different categories, based on the properties of the reinforced concrete members and the masonry infill. The frames are defined as *SD* and *nSD*, namely conforming and non-conforming to seismic design criteria, respectively. The infill walls were grouped according to two different classifications, considering the brick type and the brick material, respectively. Referring to the brick type, the infill was classified as *H* (Hollow bricks) or *S* (solid bricks), while four brick material categories were defined, namely clay brick (*CB*), concrete (*CON*), autoclaved aerated concrete (*AAC*) and other material (*Other*).

For each considered category, the median curve, η , along with the curves referred to 16th and 84th percentiles (P_{16} and P_{84} , respectively) were computed, aiming to identify the variation range of three parameters, namely the ratio between K_2/K_1 , K_{soft}/K_1 , and F_m/F_{cr} . The density distribution of the values of each considered parameter was fitted through a log-normal probability density function. A truncated distribution was assumed for the F_m/F_{cr} data, since the values lower than 1.0 are not consistent with the definition of the ratio, while in the case of K_2/K_1 , an upper limit equal to one was assumed. Referring to K_{soft}/K_1 , a standard log-normal function was used.

In **Figure 12**, the comparison of the normalized curves is provided, considering four categories, namely *CB*, *CON*, *AAC* and *Other*. The values of η , σ_{log} , P_{16} and P_{84} , obtained for the backbone parameters, F_m/F_{cr} , K_2/K_1 and K_{soft}/K_1 , are reported **Table 2**, for each category considered.

A great variability of the results was observed for all the considered parameters, particularly referring to the post peak response of the infilled frame. The value of K_{soft}/K_1 ranges between 0.00 and 0.57 when considering all the 134 tests and no correlation with the infill's and frame's type is observed. It is worth noting that the η and P_{16} values obtained for K_{soft}/K_1 are close to 0.00 (e.g. the lower bound of the log-normal distribution) for all the considered categories. The global post peak behaviour is indeed highly influenced by the post-yielding slope of the RC frame, which features either horizontal perfectly-plastic or hardening slope, both in case of *SD* and *nSD*. Hence, the softening stage is characterized by a significantly higher amount of dissipated energy, with respect to the previous stages. An additional contribution to

the dissipated energy is produced by mortar joint frictional sliding (Mehrabi et al. 1996). On the other hand, the mechanical properties of the bricks are less influent, since they are often subjected to rigid body modes in this stage. Referring to F_m/F_{cr} and K_2/K_1 , a lower scatter of the results is observed compared to K_{soft}/K_1 . The value of F_m/F_{cr} ranges between 1.05 and 5.73 when considering all the 134 tests and higher values were obtained for **CB** and **CON** with respect to **AAC** and **Other**.

Table 2 shows a negligible influence of the brick type on the median F_m/F_{cr} , when including all brick materials. On the other hand, a significantly different trend is observed analysing data referred to a specific brick material. In case of clay bricks, the median F_m/F_{cr} rises from 1.56, in **H-CB**, to 1.92, in **S-CB** (**Figure 13**). The opposite trend was obtained for the case of concrete bricks, where the median F_m/F_{cr} is equal to 1.56 and 1.85 for **S-CON** and **H-CON**, respectively. This result confirms the need of accounting for both brick type and brick material when defining the backbone F-d curve of infilled frames and highlights the utility of the proposed database.

Considering the frame type, no noticeable influence is observed for K_2/K_1 , while lower overstrength values were obtained in case of **SD** with respect to **nSD**. It is worth mentioning that the onset of damage in the infill generally occurs far below the elastic limit of the frame members, therefore, the reinforcement details have less influence on the results. On the other hand, **SD** frames might feature stiffer columns compared to **nSD**, to comply capacity design requirements, leading to a reduction of the internal forces in the infill during lateral loading and, consequently, raising the cracking limit value in the global response.

A similar analysis of the backbone parameters was conducted by De Risi et al. (2018), even though the data were not grouped in different categories. The results obtained in (De Risi et al. 2018) for F_m/F_{cr} are consistent to those provided in this work, while a significant difference is observed referring to K_2/K_1 and K_{soft}/K_1 . This feature confirms the high uncertainty in characterizing of the post-cracking and softening stage in infilled RC frames.

2.4 Infill wall response

In numerical and analytical studies, the equivalent strut formulation is a widely adopted method to assess the influence of the infill walls on the seismic response of RC buildings, both at global and local level. Referring to local interaction studies, complex modelling approaches have been recently adopted (Blasi et al. 2018a; Jeon et al. 2015; Redmond et al. 2018), to assess the reliability of existing analytical formulation in predicting the influence of the infill walls on the failure mode of the frames. An accurate estimation of the lateral response of the infill is indeed fundamental for the local interaction assessment.

Based on the piece-wise linear curves obtained in this work, the lateral force-displacement behaviour of the infill-alone was derived according to the approach by Blasi et al. (2018a). Firstly, the lateral response of the RC frame was defined, considering a bilinear hardening model, with yielding strength $V_y = 4M_y/h_c$ and ultimate strength $V_u = 4M_u/h_c$, where M_y ,

M_u and h_c are the yielding moment, the ultimate resisting moment and the height of the column, respectively. The yielding displacement, D_y , and the ultimate displacement, D_u , were calculated according to Eurocode 8 Part 3 (2005).

The obtained bilinear curve of the RC frame was subtracted to the piece-wise curve referred to the infill+frame system (Global response), to obtain the lateral behaviour of the infill-alone, as illustrated in **Figure 14**. As for the global backbone curves, the infill-alone curve was normalized to the maximum lateral strength, $F_{m,w}$, and to the corresponding displacement, $D_{m,w}$.

In the section *Piecewise_wall* of the database, all the normalized curves referred to the infill-alone response are reported. As for the section *Piecewise_Global*, the tests were grouped in different categories, namely, frame type, brick type and brick material.

In **Figure 15**, the normalized curves obtained for the infill-alone are provided, including the 16th, 50th and 84th percentiles. The categories considered in **Figure 15** are the same as those in **Figure 12**, allowing to compare the response of the global curve to that of the infill-alone.

The obtained values of the normalized parameters are provided in **Table 3**. As for the global response, a significant variability of the results was observed for all the considered parameters. The value of $K_{soft,w}/K_{I,w}$ ranges between 0.00 and 0.77 and is unrelated to the brick type or the brick material. A lower σ_{log} and, consequently, a tighter $P_{16}-P_{84}$ range is observed in case of *Other*, caused by the few available results.

A lower variability was obtained in the case of $F_{m,w}/F_{cr,w}$, which ranges between 1.02 and 6.12. As for the global response, higher values were obtained for *CB* and *CON* with respect to *AAC* and *Other*. It is worth observing that the average values of $F_{m,w}/F_{cr,w}$ are lower than those related to the global response, confirming that the maximum strength is generally achieved prior the yielding of the frame.

For almost all the considered tests, the analytical value of D_y was indeed significantly higher than the cracking displacement D_{cr} and the frame failure (either flexural or shear) occurred after the achievement of D_m . Consequently, a neglectable influence of the frame design on $F_{m,w}/F_{cr,w}$ and $K_{2,w}/K_{I,w}$ is observed comparing *SD* to *nSD*, in contrast to the infill+frame results. On the other hand, a correlation between the brick type and material and the ratio $K_{2,w}/K_{I,w}$ is observed; higher values were obtained for hollow bricks and in case of *CB* and *CON*.

According to the observed results, the influence of the frame type and the brick type on the analysed parameters is negligible, while the brick material and, consequently, its mechanical properties, is highly influent, particularly referring to $F_{m,w}/F_{cr,w}$.

3 COMPARISON WITH EMPIRICAL MODELS AND NUMERICAL STUDIES

Recent spectrum-based methods for seismic risk assessment require the definition of static pushover curves referred to a single-degree-of-freedom (SDOF) model, representing the building under investigation and including the effect of the

infill walls (Borzi et al. 2008; Dolšek and Fajfar 2004; Del Gaudio et al. 2015; De Luca et al. 2014). In regional scale analyses, the damage state bounds of a building are derived from SDOF pushover curves, which should be representative of the structural features of each archetype in the building taxonomy. Therefore, an accurate characterization of the load-displacement response of the structural system is required. In the case of infilled frames, the correct evaluation of the lateral response of the masonry wall is fundamental for the prediction of brittle failure modes in the frame members caused by the local interaction with the infill (Blasi et al. 2018a; Jeon et al. 2015).

The database results allow to define a characteristic piecewise linear shape for each infilled frame type considered, aiming to improve the effectiveness of spectrum-based pushover analyses. To this scope, a comparison between the global curves obtained from the database and numerical pushover curves obtained from the literature studies, developed with high-fidelity numerical models, is proposed. Additionally, the values of $F_{m,w}/F_{cr,w}$, $K_{2,w}/K_{1,w}$ and $K_{soft,w}/K_{1,w}$ suggested in six simplified analytical models available in the literature are compared to those obtained from the MID 1.1, aiming to identify possible improvements based on the parameters analysed in this work.

3.1 Global piece-wise monotonic backbone – comparison with numerical pushover curves

The static pushover analyses selected from the literature are referred to the studies reported in **Table 4**. The RC infilled frames analysed were classified depending on the design of the RC members (***SD*** and ***nSD***) and on the material and type of infill walls. The same nomenclature introduced in chapter 2 is used in **Table 4**. The piecewise linear fit of each pushover curve was obtained according to the same procedure described in section 2.3, and the Force-displacement coordinates were normalized to the maximum strength and to the relative displacement, respectively.

It is worth mentioning that almost all the collected numerical studies analysed gravity load-designed frames with hollow clay brick infill, confirming its wide adoption in RC buildings. As a matter of fact, the vulnerability assessment of seismic designed frames with masonry infill is less relevant, since structural damage due to the presence of the infill is generally observed in pre-code buildings. For this reason, most of the past and current studies dealing with the influence of the infill on the seismic performance of the structures, focus on gravity load designed (or non-seismic) frames.

On the other hand, the accurate evaluation of the properties of the infill walls and, consequently, the improvement of existing models defining their lateral response, can be used for code-oriented formulations aimed at considering the infill alongside the frame members as auxiliary lateral load resisting system in modern RC buildings. The comparison between the numerical curves collected from the literature and those in the database is reported in **Figure 16**.

According to the available results of the database, four categories are compared, namely ***nSD-H-CB***, ***SD-H-CB***, ***S-CB*** and ***AAC***. The curves ***P₁₆-P₈₄*** and ***η***, referred to the database, are represented with dashed and solid black lines, respectively. ***S-CB*** includes both ***nSD*** and ***SD*** frames, while ***AAC*** includes ***Hollow***, ***Solid***, ***nSD*** and ***SD***, since fewer results were available within these categories comparing to hollow clay bricks. Most of the capacity curves collected are

outside the range $P_{16}-P_{84}$, particularly referring to the softening slope in case of *nSD-H-CB*. The ratio F_m/F_{cr} is significantly underestimated with respect to the database results in the case of *S-CB*, while higher values were obtained considering *AAC* category.

A fair correspondence between the curves was only observed in the case of *SD-H-CB*, for which the ratio $F_{m,w}/F_{cr,w}$ is close to the average result from the database and the post-peak slope is approximately within the range $P_{16}-P_{84}$. Since the post-peak response of the infill is generally assumed empirically, due to its uncertain estimation, the high scatter observed is consistent with the considerations above. In the case of *AAC* walls, a lower normalized elastic stiffness is observed comparing the numerical curves to the database results. This feature is probably related to the modelling assumptions in the numerical study (Šipoš et al. 2018), which neglected the variability of $F_{m,w}/F_{cr,w}$ and $K_{2,w}/K_{1,w}$ depending on the brick material.

The results obtained show that the assumption of accurately-calibrated parameters for the lateral response of the infill, can highly influence the results of numerical analyses. The contribution of the present study to the definition of *ad-hoc* formulations, depending on the infill and on the frame type, can enhance the accuracy of the numerical analyses focused on the local interaction and global performances of infilled RC buildings.

3.2 Infill piece-wise monotonic backbone – comparison with consolidated analytical models

Aiming to assess the reliability of existing formulations used to define the lateral response of the infill walls, the normalized curves obtained for each test in the database were compared to six models available in the literature. In the considered models, the backbone parameters, $F_{m,w}/F_{cr,w}$, $K_{2,w}/K_{1,w}$ and $K_{soft,w}/K_{1,w}$, are either defined empirically or through simplified formulations, accounting for several properties of both infill wall and frame members. Therefore, in case of missing specimens' details due to lack of information in the reference, the comparison with some of the literature models was not possible.

It is worth mentioning that the model by Burton and Deierlein (2013) was developed for simulating the response of Californian RC buildings designed according to engineering practice in the early 20th century and, consequently, it is not meant to represent all the possible infilled frames configurations. Additionally, the model does not account for the influence of the infill's properties, since all the backbone parameters were defined statistically, based on laboratory tests from the literature. The same considerations apply for $F_{m,w}/F_{cr,w}$ and $K_{soft,w}/K_{1,w}$ referred to the model by Panagiotakos and Fardis (1996).

The average values of $F_{m,w}/F_{cr,w}$, $K_{2,w}/K_{1,w}$ and $K_{soft,w}/K_{1,w}$, obtained for each brick material using the literature models, are provided in **Table 5**. In case of *AAC* bricks, the evaluation of the backbone parameters was not possible for five out of six models considered, due to lack of details in several references. Additionally, the model provided by Di Trapani et

al. (2018) only allows to calculate $K_{soft,w}/K_{I,w}$, since the lateral response of the infill is simulated through a parabolic curve with linear tension softening.

In **Figure 17**, the average values of the backbone parameters, calculated using the models from the literature, are compared to the database results, for each brick material category. Referring to $F_{m,w}/F_{cr,w}$, a fair correspondence between the database and the literature results is observed, for all the models considered. On the other hand, most of the considered literature models give unconservative values for **CB** and **CON** in case of local interaction assessment, except for the model by Stavridis et al. (2017). In fact, the predicted $F_{m,w}/F_{cr,w}$ according to the analytical models is lower than the median values calculated from the database. According to Blasi et al. (2018a), the underestimation of $F_{m,w}/F_{cr,w}$ might hinder the detection of brittle failure of the columns due to the interaction with the infill, which is a major issue in case of pre-code buildings.

Referring to $K_{2,w}/K_{I,w}$, the analytical model results for **CB** and **CON** fall within the P_{16} - P_{84} range, even though a high dispersion in the database was obtained. On the contrary, a lower scatter is observed in case of **Other**, for which the models' results are significantly higher comparing to the database.

Despite the high uncertainty in the evaluation of $K_{soft,w}/K_{I,w}$, a good agreement between the database and the analytical results is observed. Except for the case of **Other**, all the analytical values are close to the median calculated among the database.

3.3 Empirical model for the equivalent strut width

In equivalent strut methods, the lateral behaviour of the infill is generally computed depending on theoretical formulations expressing the initial and the secant stiffness, K_I and K_{sec} , respectively. The value of K_I is equal to the shear stiffness of the uncracked wall (equation (1), while K_{sec} represents the axial stiffness of the post-cracking truss mechanism (equation (2).

$$K_1 = \frac{G_w t_w L_w}{H_w} \quad (1)$$

$$K_{sec} = \frac{E_w b_w t_w}{d_w} \quad (2)$$

In equations (1) and (2), E_w and G_w are the elastic and the shear modulus of the masonry prism, respectively, while b_w is the width of the equivalent strut, generally calculated depending on the properties of both frame and infill (Stafford Smith and Carter 1969). Nevertheless, b_w is affected by several parameters and its accurate evaluation using theoretical models can be challenging, leading to uncertainty in calculating K_{sec} .

Aiming to overcome this issue, a data-driven formulation expressing the width of the equivalent strut model, to be used for simplified analyses of infilled frames, is proposed. Firstly, the value of the strut width, b_w , was calculated for each infill-alone piecewise linear curve derived from the database, using equation (3).

$$b_w = \frac{K_{sec} d_w}{E_w t_w} \quad (3)$$

A multiple power-law regression of the b_w data was performed, on the basis of three predictors, namely the angle of the diagonal of the infill with respect to the horizontal direction, θ_w , the elastic modulus, E_w and the relative infill-to-frame stiffness, λ_w , evaluated according to Stafford Smith and Carter (1969).

The equation adopted for the predicted value of the strut width, $b_{w,p}$, has the form:

$$b_{w,p}(\theta_w, E_w, \lambda_w) = e^{\beta_0} \cdot \theta_w^{\beta_1} \cdot E_w^{\beta_2} \cdot \lambda_w^{\beta_3} \quad (4)$$

where $b_{w,p}$ and E_w are expressed in mm and MPa, respectively. The power-law regression parameters, β , in equation (4), were calibrated through the minimization of the sum of squared residuals. The procedure required a logarithmic transformation of equation (4), to calculate the residuals, ε , referred to each observed value of the strut width, $b_{w,i}$, according to equation (5):

$$\varepsilon_i = \ln(b_{w,i}) - \ln(b_{w,p,i}) = \ln(b_{w,i}) - \beta_0 + \beta_1 \ln \theta_{w,i} + \beta_2 \ln E_{w,i} + \beta_3 \ln \lambda_{w,i} \quad (5)$$

The sum of squared residuals was defined as:

$$\sum_{i=1}^n \varepsilon_i^2 = [\varepsilon]^T \cdot [\varepsilon] = ([Y] - [X][\beta])^T ([Y] - [X][\beta]) \quad (6)$$

In equation (6), $[\varepsilon]$, $[Y]$, $[X]$, and $[\beta]$ are the matrices including the residuals, the values of the observed $b_{w,i}$, the predictors and the regression parameters, respectively, while n is the number of data collected.

Aiming to provide a formulation depending on the brick material, two sets of power-law regression parameters to be used in equation (4) were derived (Table 6), referred to clay bricks infill and concrete bricks infill. An additional set (ALL) derived from all the data was also included. The regression was not performed for AAC and Other, due to insufficiency of records available to obtain a suitable regression.

Figure 18 reports comparisons between the observed and the predicted values of the strut width, calculated using the developed empirical equations. The coefficients of determination, R^2 , obtained do not indicate a high accuracy of the model in predicting the observed values of b_w , due to the great dispersion of the data. On the other hand, the uncertainty of the estimation is consistent with the results of similar studies on data-driven models (Huang et al. 2020). The wide number of parameters influencing the post-cracking behaviour of the infill cause challenges in the definition of accurate equation for the evaluation of the strut width. For this reason, the regression of laboratory test data represents a reliable alternative to simplified theoretical models, which might be too succinct or inconsistent with the experimental findings.

4 CONCLUSIONS

The tests collected in this work were accurately selected among the literature studies on infilled frames, to obtain a comprehensive analysis of the infill wall's behaviour depending on several parameters, related to both masonry wall and

frame members. The database entirely regards reinforced concrete frames with unreinforced masonry infill and purposely neglects other categories, to avoid major dispersion of the data.

The envelope of the experimental load-displacement response of the infilled frame is approximated through a piece-wise linear model, whose characterization was analysed depending on the brick material, the brick type and the frame type. A significant influence of the brick material on the ratio between the cracking strength and the maximum lateral strength in the piecewise curve is observed. On the other hand, the post-peak slope seems not clearly related to the considered parameters.

The evaluation of the response of the infill-alone by subtracting the lateral behaviour of the reinforced concrete frame to the curve referred to the whole system allows to focus on the masonry wall's parameters and confirms the correlation between the brick material and the ratio between the peak and the cracking strength.

The results of numerical pushover studies on reinforced concrete buildings are assessed by comparing the parameters characterizing the pushover curve to the database results. For all the considered parameters, a significant difference between the numerical and the database results is observed. Moreover, six widely adopted analytical models are revised based on the database results. Despite the considered models are suitable in approximating of the load-displacement response of infilled frames, the influence of the brick material on the ratio between the peak to cracking strength is generally neglected. This feature can cause underestimation of the maximum strength and leads to unconservative results when analysing the failure of the columns due to the interaction with the infill.

The median values of the overstrength provided in this study, calculated among the data collected for each brick material, could represent a suitable improvement to existing formulations. Additionally, the empirical model calibrated through power law multiple regression of the data can be used in simplified analyses of infilled frames for the calibration of the equivalent strut, depending on the brick material.

The database developed herein is meant to provide comprehensive information for the research on infilled RC frames. The accurate analysis of the interaction between masonry infill and reinforced concrete frames is fundamental for the vulnerability assessment of existing buildings and is strictly related to the reliability in the definition of the lateral behaviour of the infill. Furthermore, the results presented in this work can be used to develop suitable code-oriented formulations, to be adopted for the design of new buildings.

446 DATA AVAILABILITY STATEMENT

447 All data used during the study, including the Excel spreadsheet file of the Masonry Infill Database MID 1.1, are
 448 available at the University of Bristol data repository, data.bris, at
 449 <https://doi.org/10.5523/bris.71oex4uyxye925b8fai0v1qk5>, in accordance with funder data retention policies.

450 ACKNOWLEDGEMENTS

451 The second author acknowledge the support of the Leverhulme Trust (RPG-2017-006, GENESIS project). The database
 452 MID 1.1 is used to produce all figures and tables in this publication.

- 454 ACI 318-14. (2014). *ACI 318-14 - Building Code Requirements for Structural Concrete*. American Concrete Institute.
- 455 Al-Chaar, G. K., Issa, M., and Sweeney, S. (2002). "Behavior of Masonry-Infilled Nonductile Reinforced Concrete
456 Frames." *Journal of Structural Engineering*, 128(8), 1055–1063.
- 457 Al-Naghi, A. A. A., Rahman, M. K., Al-Amoudi, O. S. B., and Al-Dulaijan, S. U. (2020). "Thermal Performance
458 Evaluation of Walls with AAC Blocks, Insulating Plaster, and Reflective Coating." *Journal of Energy Engineering*,
459 146(2), 1–14.
- 460 Al-Nimry, H. S. (2014). "Quasi-Static Testing of RC Infilled Frames and Confined Stone-Concrete Bearing Walls."
461 *Journal of Earthquake Engineering*, 18(1), 1–23.
- 462 Angel, R., Abrams, D. P., Shapiro, D., Uzarski, J., and Webster, M. (1994). "Behavior of Reinforced Concrete Frames
463 With Masonry Infills." University of Illinois.
- 464 ASCE/SEI 41-17. (2017). *Seismic Evaluation and Retrofit of Existing Buildings*. American Society of Civil Engineers.
- 465 Baran, M., and Sevil, T. (2010). "Analytical and experimental studies on infilled RC frames." *International Journal of
466 the Physical Sciences*, 5(13), 1981–1998.
- 467 Basha, S. H., and Kaushik, H. B. (2012). "Evaluation of Shear Demand on Columns of Masonry Infilled Reinforced
468 Concrete Frames." *15th World Conference on Earthquake Engineering*, Lisboa, Portugal.
- 469 Basha, S. H., and Kaushik, H. B. (2016). "Suitability of fly ash brick masonry as infill in reinforced concrete frames."
470 *Materials and Structures*, 49, 3831–3845.
- 471 Bazan, E., and Meli, R. (1980). "Seismic analysis of structures with masonry walls." *Procedures in 7th World Conf. on
472 Earthquake Engineering*, Istanbul, Turkey, 633–640.
- 473 Biondi, S., Colangelo, F., and Nuti, C. (2000). *La risposta sismica dei telai con tamponature murarie. CNR-Gruppo
474 Nazionale per la Difesa dai Terremoti-Roma*.
- 475 Blasi, G. (2019). "Seismic performances of Non-Structural Components: influence on the structural behaviour and
476 vulnerability assessment." University of Salento, Italy.
- 477 Blasi, G., De Luca, F., and Aiello, M. A. (2018a). "Brittle failure in RC masonry infilled frames: The role of infill
478 overstrength." *Engineering Structures*, Elsevier, 177, 506–518.
- 479 Blasi, G., Perrone, D., and Aiello, M. A. (2018b). "Fragility functions and floor spectra of RC masonry infilled frames:
480 influence of mechanical properties of masonry infills." *Bulletin of Earthquake Engineering*, Springer Netherlands,
481 16, 6105–6130.
- 482 Blasi, G., Perrone, D., and Aiello, M. A. (2020). "Influence of the modelling approach on the failure modes of RC Infilled
483 frames under seismic actions." *Lecture Notes in Civil Engineering - Proceedings of Italian Concrete Days 2018*,
484 Springer.
- 485 Borzi, B., Pinho, R., and Crowley, H. (2008). "Simplified pushover-based vulnerability analysis for large-scale
486 assessment of RC buildings." *Engineering Structures*, 30(3), 804–820.
- 487 Bose, S., and Rai, D. C. (2014). "Behavior of AAC infilled RC frame under lateral loading." *10th U.S. National
488 Conference on Earthquake Engineering*, Anchorage, Alaska.
- 489 Burton, H., and Deierlein, G. (2013). "Simulation of Seismic Collapse in Non-Ductile Reinforced Concrete Frame
490 Buildings with Masonry Infills." *Journal of Structural Engineering*, 140(8), A4014016.
- 491 Calvi, G. M., and Bolognini, D. (2001). "Seismic Response of Reinforced Concrete Frames Infilled With Weakly
492 Reinforced Masonry Panels." *Journal of Earthquake Engineering*, 5(2), 153–185.
- 493 Calvi, G. M., Bolognini, D., and Penna, A. (2004). "Seismic performance of masonry-infilled R.C. Frames: Benefits of
494 slight reinforcements." *6th Portuguese Congress on Seismology and Earthquake Engineering*, 253–276.
- 495 Cavaleri, L., and Di Trapani, F. (2014). "Cyclic response of masonry infilled RC frames: Experimental results and
496 simplified modeling." *Soil Dynamics and Earthquake Engineering*, 65, 224–242.
- 497 Cavaleri, L., and Di Trapani, F. (2015). "Prediction of the additional shear action on frame members due to infills."
498 *Bulletin of Earthquake Engineering*, 13(5), 1425–1454.
- 499 Cavaleri, L., Di Trapani, F., Asteris, P. G., and Sarhosis, V. (2017). "Influence of column shear failure on pushover based
500 assessment of masonry infilled reinforced concrete framed structures: A case study." *Soil Dynamics and Earthquake
501 Engineering*, 100, 98–112.
- 502 Celarec, D., Ricci, P., and Dolšek, M. (2012). "The sensitivity of seismic response parameters to the uncertain modelling

variables of masonry-infilled reinforced concrete frames.” *Engineering Structures*, 35, 165–177.

Çelebi, M., Bazzurro, P., Chiaraluce, L., Clemente, P., Decanini, L., Desortis, A., Ellsworth, W., Gorini, A., Kalkan, E., Marcucci, S., Milana, G., Mollaioli, F., Olivieri, M., Paolucci, R., Rinaldis, D., Rovelli, A., Sabetta, F., and Stephens, C. (2010). “Recorded motions of the 6 April 2009 Mw6.3 L’Aquila, Italy, earthquake and implications for building structural damage: Overview.” *Earthquake Spectra*, 26(3), 651–684.

Chrysostomou, C. Z., Gergely, P., and Abel, J. F. (2002). “A six-strut model for nonlinear dynamic analysis of steel infilled frames.” *International Journal of Structural Stability and Dynamics*, 2(3), 335–353.

Colangelo, F. (1996). “Pseudodynamic tests on brick-infilled RC frames.” *11th World Conference on Earthquake Engineering*, Acapulco, Mexico.

Colangelo, F. (2003). “Experimental Evaluation of Member-By-Member Models and Damage Indices for Infilled Frames.” *Journal of Earthquake Engineering*, 7(1), 25–50.

Colangelo, F. (2005). “Pseudo-dynamic seismic response of reinforced concrete frames infilled with non-structural brick masonry.” *Earthquake Engineering and Structural Dynamics*, 34, 1219–1241.

Crisafulli, F. J. (1997). “Seismic behaviour of reinforced concrete structures with masonry infills.” University of Canterbury, New Zealand.

Crisafulli, F. J., Carr, A. J., and Park, R. (2005). “Experimental response of framed masonry structures designed with new reinforcing details.” *Bulletin of the New Zealand Society for Earthquake Engineering*, 38(1), 19–32.

Decanini, L. D., De Sortis, A., Goretti, A., Liberatore, L., Mollaioli, F., and Bazzurro, P. (2004). “Performance of Reinforced Concrete Buildings During the 2002 Molise, Italy, Earthquake.” *Earthquake Spectra*, 20(S1), S221–S255.

Deierlein, G. G., Reinhorn, A. M., and Willford, M. R. (2010). *Nonlinear Structural Analysis For Seismic Design - A Guide for Practicing Engineers*. US, 36.

Del Gaudio, C., Ricci, P., Verderame, G. M., and Manfredi, G. (2015). “Development and urban-scale application of a simplified method for seismic fragility assessment of RC buildings.” *Engineering Structures*, Elsevier Ltd, 91, 40–57.

De Luca, F., Blasi, G., Perrone, D., and Aiello, M. A. (2020). “MASONRY INFILL DATABASE MID 1.1.” <<https://doi.org/10.5523/bris.71oex4uyxye925b8fai0v1qk5>>.

De Luca, F., Giordano, N., Gryc, H., Hulme, L., McCarthy, C., Sanderson, V., and Sextos, A. (2019). “Nepalese School Building Stock and Implications on Seismic Vulnerability Assessment.” *2nd International Conference on Earthquake Engineering and Post Disaster Reconstruction Planning*, Bhaktapur, Nepal.

De Luca, F., Kythreotis, S., Werner, M. J., and Verdon, J. P. (2017). “Natural earthquakes as proxies for induced seismic hazard and risk: comparing peak and cyclic inelastic response.” *16th World Conference on Earthquake*, Santiago Chile.

De Luca, F., Morciano, E., Perrone, D., and Aiello, M. A. (2016). “Masonry Infilled RC Frame Experimental Database.” *Proceeding of CTE conference*, Rome, Italy.

De Luca, F., Vamvatsikos, D., and Iervolino, I. (2013). “Near-optimal piecewise linear fits of static pushover capacity curves for equivalent SDOF analysis.” *Earthquake Engineering and Structural Dynamics*, 42, 523–543.

De Luca, F., Verderame, G. M., Gómez-Martínez, F., and Pérez-García, A. (2014). “The structural role played by masonry infills on RC building performances after the 2011 Lorca, Spain, earthquake.” *Bulletin of Earthquake Engineering*, 12(5), 1999–2026.

De Risi, M. T., Del Gaudio, C., Ricci, P., and Verderame, G. M. (2018). “In-plane behaviour and damage assessment of masonry infills with hollow clay bricks in RC frames.” *Engineering Structures*, 168, 257–275.

Di Trapani, F. (2014). “Masonry infilled RC frames: Experimental results and development of predictive techniques for the assessment of seismic response.” Università degli Studi di Palermo.

Di Trapani, F., Bertagnoli, G., Ferrotto, M. F., and Gino, D. (2018). “Empirical Equations for the Direct Definition of Stress–Strain Laws for Fiber-Section-Based Macromodeling of Infilled Frames.” *Journal of Engineering Mechanics*, 144(11), 04018101.

Di Trapani, F., Bolis, V., Basone, F., and Preti, M. (2020). “Seismic reliability and loss assessment of RC frame structures with traditional and innovative masonry infills.” *Engineering Structures*, Elsevier, 208, 110306.

Dolšek, M., and Fajfar, P. (2001). “Soft storey effects in uniformly infilled reinforced concrete frames.” *Journal of Earthquake Engineering*, 5(1), 1–12.

Dolšek, M., and Fajfar, P. (2004). “IN2 - A simple alternative for IDA.” *13th World Conference on Earthquake*

555 *Engineering*, Vancouver, Canada.

556 Dolšek, M., and Fajfar, P. (2005). "Simplified non-linear seismic analysis of infilled reinforced concrete frames."
557 *Earthquake Engineering and Structural Dynamics*, 34, 49–66.

558 Dolšek, M., and Fajfar, P. (2008). "The effect of masonry infills on the seismic response of a four-storey reinforced
559 concrete frame - a deterministic assessment." *Engineering Structures*, 30(7), 1991–2001.

560 EMS-98. (1998). *European Macroseismic Scale 1998*. European Seismological Commission.

561 EN 1992-1-1. (2004). *Eurocode 2 - Design of concrete structures - Part 1-1: General rules and rules for buildings*.
562 European Standard.

563 EN 1998-1. (2005). *Eurocode 8 - Design of structures for earthquake resistance - Part 1: General rules, seismic actions*
564 *and rules for buildings*. European Standard.

565 EN 1998-3. (2005). *Eurocode 8 - Design of structures for earthquake resistance - Part 3: Assessment and retrofitting of*
566 *buildings*. European Standard.

567 FEMA 306. (1998). *Evaluation of earthquake damaged concrete and masonry wall buildings*. Federal Emergency
568 Management Agency.

569 FEMA 356. (2000). *FEMA 356 Prestandard and Commentary for the Seismic Rehabilitation of Building*. Federal
570 Emergency Management Agency.

571 Fiore, A., Porco, F., Raffaele, D., and Uva, G. (2012). "About the influence of the infill panels over the collapse
572 mechanisms actived under pushover analyses: Two case studies." *Soil Dynamics and Earthquake Engineering*,
573 Elsevier, 39, 11–22.

574 Ganz, H. R. (2003). *Post-Tensioned Masonry structures*. VSL International LTD.

575 Haris, I., and Farkas, G. (2018). "Experimental results on masonry infilled RC frames for monotonic increasing and cyclic
576 lateral load." *Periodica Polytechnica Civil Engineering*, 62(3), 772–782.

577 Huang, H., Burton, H. V., and Sattar, S. (2020). "Development and Utilization of a Database of Infilled Frame
578 Experiments for Numerical Modeling." *Journal of Structural Engineering*, 146(6), 04020079.

579 Huang, Q., Guo, Z., and Kuang, J. S. (2016). "Designing infilled reinforced concrete frames with the 'strong frame-weak
580 infill' principle." *Engineering Structures*, 123, 341–353.

581 Imran, I., and Aryanto, A. (2009). "Behavior of Reinforced Concrete Frames In-Filled with Lightweight Materials Under
582 Seismic Loads." *Civil Engineering Dimension*, 11(2), 69–77.

583 Jeon, J.-S., Park, J.-H., and DesRoches, R. (2015). "Seismic fragility of lightly reinforced concrete frames with masonry
584 infill." *Earthquake Engineering and Structural Dynamics*, 44, 1783–1803.

585 Kakaletsis, D. (2011). "Comparison of CFRP and alternative seismic retrofitting techniques for bare and infilled RC
586 frames." *Journal of Composites for Construction*, 15(4), 565–577.

587 Kakaletsis, D. J., and Karayannis, C. G. (2008). "Influence of masonry strength and openings on infilled R/C frames
588 under cycling loading." *Journal of Earthquake Engineering*, 12(2), 197–221.

589 Kyriakides, M. A. (2011). "Seismic Retrofit of Unreinforced masonry infills in non-ductile reinforced concrete frames
590 using engineered cementitious composites." Stanford University.

591 Liauw, T.-C., and Kwan, K.-H. (1984). "Nonlinear behaviour of non-integral infilled frames." *Computers and Structures*,
592 18(3), 551–560.

593 Liberatore, L., Noto, F., Mollaioli, F., and Franchin, P. (2018). "In-plane response of masonry infill walls: Comprehensive
594 experimentally-based equivalent strut model for deterministic and probabilistic analysis." *Engineering Structures*,
595 167, 533–548.

596 Mainstone, R. J. (1971). "On the stiffnesses and strengths of infilled frames." *Proceedings of the Institution of Civil*
597 *Engineers*, 49(2), 57–90.

598 Manfredi, G., Prota, A., Verderame, G. M., De Luca, F., and Ricci, P. (2014). "2012 Emilia earthquake, Italy: reinforced
599 concrete buildings response." *Bulletin of Earthquake Engineering*, 12(5), 2275–2298.

600 Mehrabi, A. B., Shing, P. B., Schuller, M. P., and Noland, J. L. (1994). "Performance of Masonry-Infilled R/C frames
601 under in-plane lateral loads." University of Colorado.

602 Mehrabi, A. B., Shing, P. B., Schuller, M. P., and Noland, J. L. (1996). "Experimental Evaluation of Masonry In-filled
603 RC frames." *Journal of Structural Engineering*, 122(3), 228–237.

604 Milanesi, R. R., Morandi, P., and Magenes, G. (2018). "Local effects on RC frames induced by AAC masonry infills

through FEM simulation of in-plane tests." *Bulletin of Earthquake Engineering*, Springer Netherlands, 16(9), 4053–4080.

Panagiotakos, T. B., and Fardis, M. N. (1996). "Seismic Response of Infilled RC Frame Structures." *11th World Conference on Earthquake Engineering*, Acapulco, Mexico.

Pantò, B., Calì, I., and Lourenço, P. B. (2017). "Seismic safety evaluation of reinforced concrete masonry infilled frames using macro modelling approach." *Bulletin of Earthquake Engineering*, 15(9), 3871–3895.

Peng, Q., Zhou, X., and Yang, C. (2018). "Influence of connection and constructional details on masonry-infilled RC frames under cyclic loading." *Soil Dynamics and Earthquake Engineering*, 108, 96–110.

Penna, A., Magenes, G., Calvi, G. M., and Costa, A. (2008). "Seismic performance of AAC infill and bearing walls with different reinforcement solutions." *14th International Brick & Block Masonry Conference*, Sydney, Australia.

Perrone, D., Leone, M., and Aiello, M. A. (2016). "Evaluation of the infill influence on the elastic period of existing RC frames." *Engineering Structures*, 123, 419–433.

Perrone, D., Leone, M., and Aiello, M. A. (2017). "Non-linear behaviour of masonry infilled RC frames: Influence of masonry mechanical properties." *Engineering Structures*, 150, 875–891.

Pires, F., and Carvalho, E. C. (1992). "The behaviour of infilled concrete frames under horizontal cyclic loading." *10th world Conference on Earthquake Engineering*, Balkema, Rotterdam, 3419–3422.

Polese, M., Verderame, G. M., Mariniello, C., Iervolino, I., and Manfredi, G. (2008). "Vulnerability analysis for gravity load designed RC buildings in Naples - Italy." *Journal of Earthquake Engineering*, 12(S2), 234–245.

Polyakov, S. V. (1960). *On the interaction between masonry filler walls and enclosing frame when loading in the plane of the wall. Translations in earthquake Engineering*. EERI, Earthquake Engineering Research Institute, San Francisco, California.

Porco, F., Fiore, A., Uva, G., and Raffaele, D. (2015). "The influence of infilled panels in retrofitting interventions of existing reinforced concrete buildings: a case study." *Structure and Infrastructure Engineering*, 11(2), 162–175.

Pujol, S., and Fick, D. (2010). "The test of a full-scale three-story RC structure with masonry infill walls." *Engineering Structures*, 32(10), 3112–3121.

Redmond, L., Stavridis, A., Kahn, L., and DesRoches, R. (2018). "Finite-Element Modeling of Hybrid Concrete-Masonry Frames Subjected to In-Plane Loads." *Journal of Structural Engineering*, 144(1), 04017178.

Ricci, P., De Luca, F., and Verderame, G. M. (2011). "6th April 2009 L'Aquila earthquake, Italy: Reinforced concrete building performance." *Bulletin of Earthquake Engineering*, 9(1), 285–305.

Ricci, P., De Risi, M. T., Verderame, G. M., and Manfredi, G. (2016). "Procedures for calibration of linear models for damage limitation in design of masonry-infilled RC frames." *Earthquake Engineering and Structural Dynamics*, 45(8), 1315–1335.

Rossetto, T., and Elnashai, A. (2005). "A new analytical procedure for the derivation of displacement-based vulnerability curves for populations of RC structures." *Engineering Structures*, 27, 397–409.

Salmanpour, A., Mojsilovic, N., and Schwartz, J. (2012). "Experimental Study of the Deformation Capacity of Structural Masonry." *12th Canadian Masonry Symposium*, Vancouver, British Columbia.

Schwarz, S., Hanaor, A., and Yankelevsky, D. Z. (2015). "Experimental Response of Reinforced Concrete Frames With AAC Masonry Infill Walls to In-plane Cyclic Loading." *Structures*, 3, 306–319.

Sezen, H., Whittaker, A. S., Elwood, K. J., and Mosalam, K. M. (2003). "Performance of reinforced concrete buildings during the August 17, 1999 Kocaeli, Turkey earthquake, and seismic design and construction practise in Turkey." *Engineering Structures*, 25(1), 103–114.

Šipoš, T. K., Hadzima-Nyarko, M., Miličević, I., and Marin Grubisic. (2018). "Structural Performance Levels for Masonry Infilled Frames." *16th European Conference on Earthquake Engineering*, Thessaloniki, Greece.

Šipoš, T. K., Sigmund, V., and Hadzima-Nyarko, M. (2013). "Earthquake performance of infilled frames using neural networks and experimental database." *Engineering Structures*, 51, 113–127.

Skafida, S., Koutas, L., Bousias, S. N., Skafida, S., Koutas, L., and Bousias, S. N. (2014). "Analytical Modeling of Masonry Infilled RC Frames and Verification with Experimental Data." *Journal of Structures*, 2014, 1–17.

Stafford Smith, B., and Carter, C. (1969). "A method of Analysis for Infilled Frames." *Proceedings of the Institution of Civil Engineers*, 44(1), 31–48.

Stavridis, A., Martin, J., and Bose, S. (2017). "Updating the ASCE 41 provisions for infilled RC frames." *2017 Structural Engineers Association of California (SEAOC) Convention*, Sacramento, US.

- 656 Teguh, M. (2017). "Experimental Evaluation of Masonry Infill Walls of RC Frame Buildings Subjected to Cyclic Loads."
657 *Procedia Engineering*, 171, 191–200.
- 658 Uva, G., Porco, F., and Fiore, A. (2012). "Appraisal of masonry infill walls effect in the seismic response of RC framed
659 buildings: A case study." *Engineering Structures*, Elsevier Ltd, 34, 514–526.
- 660 Varum, H., Rodrigues, H., and Costa, A. (2005). "Numerical model to account for the influence of infill masonry on the
661 RC structures behaviour." *XII Portuguese Society Meeting/ III International Material Symposium*.
- 662 Verderame, G. M., De Luca, F., Ricci, P., and Manfredi, G. (2011). "Preliminary analysis of a soft-storey mechanism
663 after the 2009 L'Aquila earthquake." *Earthquake Engineering and Structural Dynamics*, 40(8), 925–944.
- 664 Verderame, G. M., Ricci, P., De Luca, F., Del Gaudio, C., and De Risi, M. T. (2014). "Damage scenarios for RC buildings
665 during the 2012 Emilia (Italy) earthquake." *Soil Dynamics and Earthquake Engineering*, 66, 385–400.
- 666 Zovkic, J., Sigmund, V., and Guljas, I. (2013). "Cyclic testing of a single bay reinforced concrete frames with various
667 types of masonry infill." *Earthquake Engineering and Structural Dynamics*, 42, 1131–1149.
- 668 Zovkić, J., Sigmund, V., and Guljaš, I. (2012). "Testing of R/C frames with masonry infill of various strength." *15th*
669 *World Conference on Earthquake Engineering*, Lisboa (PT).