Crawford, A. O., Cavalli, G., Howlin, B. J., & Hamerton, I. (2016). Improving the hydrolytic stability of aryl cyanate esters by examining the effects of extreme environments on polycyanurate copolymers. *Reactive and Functional Polymers*, 109, 104-111.
<https://doi.org/10.1016/j.reactfunctpolym.2016.10.007>

Other version

License (if available):
CC BY-NC-ND

Link to published version (if available):
[10.1016/j.reactfunctpolym.2016.10.007](https://doi.org/10.1016/j.reactfunctpolym.2016.10.007)

[Link to publication record in Explore Bristol Research](#)
PDF-document

This is the accepted author manuscript (AAM). The final published version (version of record) is available online via Elsevier at <http://dx.doi.org/10.1016/j.reactfunctpolym.2016.10.007>. Please refer to any applicable terms of use of the publisher.

University of Bristol - Explore Bristol Research

General rights

This document is made available in accordance with publisher policies. Please cite only the published version using the reference above. Full terms of use are available:
<http://www.bristol.ac.uk/red/research-policy/pure/user-guides/ebr-terms/>

Improving the Hydrolytic Stability of Aryl Cyanate Esters by Examining the Effects of Extreme Environments on Polycyanurate Copolymers

Alasdair O. Crawford, Gabriel Cavalli, Brendan J. Howlin, and Ian Hamerton*

Fig. S1. Images of selected blends between 1-3.

Fig. S2. $[I_x-2_y]$ H₂O absorbed (%) vs. time (√hrs) at 75 % RH

Fig. S3. $[3_x-1_y]$ H₂O absorbed (%) vs. time ($\sqrt{\text{hrs}}$) at 75 % RH

Fig. S4. $[3_x-2_y]$ H₂O absorbed (%) vs. time ($\sqrt{\text{hrs}}$) at 75 % RH

Fig. S5. Spectral analysis of $[3_x-1_y]$

Fig. S6. Spectral analysis of $[3_x-2_y]$

Fig. S7. $[I_{x-2y}]$ H₂O absorbed (%) vs. time ($\sqrt{\text{hrs}}$)

Fig. S8. $[3_x-1_y]$ H₂O absorbed (%) vs. time ($\sqrt{\text{hrs}}$)

Fig. S9. $[3_x-2_y]$ H₂O absorbed (%) vs. time ($\sqrt{\text{hrs}}$)

Fig. S10. DMTA data for unexposed (black), RH (red) and immersion (blue) for the blend [I₅₀-2₅₀] showing storage modulus as a function of temperature.

Fig. S11 DMTA data for I_{70-230} (top) and $[I_{70-230}]$ (bottom) showing storage and loss moduli as a function of temperature.

Fig. S12 High resolution images of outgassing in [(1)₅₀-(2)₅₀]

Fig. S13 Top view (above) and side view (below) of [(3)₉₀-(2)₁₀] following exposure and DMTA.

Fig. S14 Basic (left) and Acidic (right) environments with immersed [(3)₈₀-(2)₂₀] (top), surface etching of [(3)₈₀-(2)₂₀] (bottom) following exposure to NaOH for 3192 hours.

Table S1. Mass uptakes observed in 75.3 % RH studies

Material	Initial mass (M ₀)/g	Final mass (M _i)/g	H ₂ O absorption/%
<i>I</i> ₅₀ - <i>2</i> ₅₀	2.3344	2.3545	0.85
<i>I</i> ₆₀ - <i>2</i> ₄₀	1.9844	1.9996	0.76
<i>I</i> ₇₀ - <i>2</i> ₃₀	1.9211	1.9370	0.82
<i>I</i> ₈₀ - <i>2</i> ₂₀	1.1480	1.1572	0.80
<i>I</i> ₉₀ - <i>2</i> ₁₀	1.3742	1.3843	0.73
<i>3</i> ₅₀ - <i>I</i> ₅₀	2.1897	2.2040	0.65
<i>3</i> ₆₀ - <i>I</i> ₄₀	1.5209	1.5320	0.72
<i>3</i> ₇₀ - <i>I</i> ₃₀	1.9007	1.9163	0.81
<i>3</i> ₈₀ - <i>I</i> ₂₀	2.1262	2.1485	1.04
<i>3</i> ₉₀ - <i>I</i> ₁₀	1.7388	1.7583	1.11
<i>3</i> ₅₀ - <i>2</i> ₅₀	1.4718	1.4858	0.94
<i>3</i> ₆₀ - <i>2</i> ₄₀	1.9115	1.9301	0.96
<i>3</i> ₇₀ - <i>2</i> ₃₀	1.6132	1.6304	1.06
<i>3</i> ₈₀ - <i>2</i> ₂₀	1.7078	1.7273	1.13
<i>3</i> ₉₀ - <i>2</i> ₁₀	1.9839	2.0132	1.46

Table S2. Mass uptake observed in direct immersion studies

Material	Initial mass (M ₀) /g	Final mass (M _i) /g	H ₂ O absorption/ %
<i>1₅₀-2₅₀</i>	8.9461	9.0833	1.51
<i>1₆₀-2₄₀</i>	13.5747	13.8366	1.89
<i>1₇₀-2₃₀</i>	10.6314	10.827	1.81
<i>1₈₀-2₂₀</i>	12.9197	13.1641	1.86
<i>1₉₀-2₁₀</i>	7.5177	7.6385	1.58
<i>3₅₀-1₅₀</i>	17.2649	17.7285	2.61
<i>3₆₀-1₄₀</i>	17.3742	17.8680	2.76
<i>3₇₀-1₃₀</i>	12.7562	13.1457	2.96
<i>3₈₀-1₂₀</i>	15.4618	15.9268	2.92
<i>3₉₀-1₁₀</i>	13.8261	14.2588	3.03
<i>3₅₀-2₅₀</i>	13.5108	13.8650	2.55
<i>3₆₀-2₄₀</i>	17.2138	17.6260	2.34
<i>3₇₀-2₃₀</i>	15.4747	15.9267	2.84
<i>3₈₀-2₂₀</i>	11.8710	12.2167	2.83
<i>3₉₀-2₁₀</i>	15.6982	16.1960	3.07

Table S3. Thermogravimetric data for cured binary cyanate ester blends as determined by TGA (nitrogen, 10 K/minute)

Sample	Mass Loss at Temperature (°C)							Y _C (%)
	5 %	10 %	20 %	30 %	40 %	50 %	60 %	
<i>1</i>	413	423	428	435	458	538	575	1.83
<i>2</i>	417	422	430	452	530	571	588	1.89
<i>3</i>	423	434	522	595	620	635	650	1.76
<i>1</i>₅₀-<i>2</i>₅₀	414	422	427	436	484	549	576	2.03
<i>1</i>₆₀-<i>2</i>₄₀	411	419	421	422	429	470	551	1.54
<i>1</i>₇₀-<i>2</i>₃₀	416	425	427	436	470	542	570	1.45
<i>1</i>₈₀-<i>2</i>₂₀	413	425	430	438	489	552	579	1.22
<i>1</i>₉₀-<i>2</i>₁₀	410	424	428	435	458	530	552	1.76
<i>1</i>₃₀-<i>2</i>₅₀	416	425	441	522	572	595	608	1.38
<i>1</i>₆₀-<i>2</i>₄₀	419	426	460	552	592	610	622	1.59
<i>3</i>₇₀-<i>1</i>₃₀	420	429	498	573	604	621	635	1.65
<i>3</i>₈₀-<i>1</i>₂₀	420	431	498	578	609	625	640	1.33
<i>3</i>₉₀-<i>1</i>₁₀	419	434	515	585	603	619	633	1.67
<i>3</i>₅₀-<i>2</i>₅₀	420	430	484	558	592	608	621	1.41
<i>3</i>₆₀-<i>2</i>₄₀	420	432	489	560	594	612	624	1.75
<i>3</i>₇₀-<i>2</i>₃₀	408	423	429	487	555	587	604	1.47
<i>3</i>₈₀-<i>2</i>₂₀	420	434	513	574	603	619	633	1.58
<i>3</i>₉₀-<i>2</i>₁₀	418	433	508	566	597	614	628	1.34

Y_C = Char yield measured at 800 °C

Table S4. Mass uptakes observed in acid/base studies

Material	Initial mass (M ₀) /g		Final mass (M _i) /g		Mass change /%	
	H ₂ SO ₄	NaOH	H ₂ SO ₄	NaOH	H ₂ SO ₄	NaOH
<i>I</i>₅₀₋₂₅₀	2.086	2.208	2.1097	2.2348	+1.01	+1.01
<i>I</i>₆₀₋₂₄₀	1.672	1.449	1.6915	1.4670	+1.01	+1.01
<i>I</i>₇₀₋₂₃₀	2.289	2.363	2.1350	2.3897	+1.01	+1.01
<i>I</i>₈₀₋₂₂₀	1.892	1.768	1.9118	1.7904	+1.01	+1.02
<i>I</i>₉₀₋₂₁₀	0.641	0.481	0.6460	0.4865	+1.01	+1.01
<i>3</i>₅₀₋₁₅₀	1.776	1.750	1.7950	1.7700	+1.01	+1.01
<i>3</i>₆₀₋₁₄₀	1.816	2.370	1.8365	2.4016	+1.01	+1.01
<i>3</i>₇₀₋₁₃₀	2.217	1.458	2.2395	1.4773	+1.01	+1.01
<i>3</i>₈₀₋₁₂₀	1.909	2.427	1.9307	2.4620	+1.01	+1.01
<i>3</i>₉₀₋₁₁₀	1.720	1.889	1.7388	1.9242	+1.01	+1.02
<i>3</i>₅₀₋₂₅₀	1.254	1.327	1.2648	1.3380	+1.01	+1.01
<i>3</i>₆₀₋₂₄₀	1.335	0.970	1.3462	0.9810	+1.01	+1.01
<i>3</i>₇₀₋₂₃₀	1.930	2.052	1.946	2.0761	+1.01	+1.01
<i>3</i>₈₀₋₂₂₀	1.703	1.671	1.7265	1.6909	+1.01	+1.01
<i>3</i>₉₀₋₂₁₀	1.523	1.398	1.5408	1.4282	+1.01	+1.02