



Vardanega, P., Feng, S., & Shephard, C. (2017). Some recent research on the hydraulic conductivity of road materials. In A. Loizos, I. Al-Qadi, & T. Scarpas (Eds.), *Bearing Capacity of Roads, Railways and Airfields: Proceedings of the 10th International Conference on the Bearing Capacity of Roads, Railways and Airfields (BCRRA 2017), June 28-30, 2017, Athens, Greece* (pp. 135-142). CRC Press.
<https://www.routledge.com/Bearing-Capacity-of-Roads-Railways-and-Airfields-Proceedings-of-the-10th/Loizos-Al-Qadi-Scarpas/p/book/9781138295957>

Peer reviewed version

[Link to publication record on the Bristol Research Portal](#)
PDF-document

This is the author accepted manuscript (AAM). The final published version (version of record) is available via Taylor & Francis. Please refer to any applicable terms of use of the publisher.

University of Bristol – Bristol Research Portal

General rights

This document is made available in accordance with publisher policies. Please cite only the published version using the reference above. Full terms of use are available:
<http://www.bristol.ac.uk/red/research-policy/pure/user-guides/brp-terms/>

Some recent research on the hydraulic conductivity of road materials

P. J. Vardanega, S. Feng and C. J. Shephard
University of Bristol, Bristol, United Kingdom

ABSTRACT: Hydraulic conductivity is an important material parameter for pavement engineers. The ability to make a priori estimates of the coefficient of permeability of road pavement materials is very useful when studying issues of pavement durability and predicting pavement performance. This paper presents two laboratory databases assembled from data sourced from the literature. Using a database of permeability tests on fine-grained soils, the ability of the Kozeny-Carman void ratio function to interpret the data is examined alongside a simple power-law relationship. A second database of permeability measurements on asphalt concrete specimens is used to re-examine the ‘representative pore size’ concept as a method of predicting the coefficient of permeability. The influence of nominal maximum aggregate size (NMAS) on the coefficient of permeability is also studied.

1 INTRODUCTION

1.1 Literature review

The hydraulic conductivity of road building materials is a useful engineering parameter and should be considered when asphalt concrete (AC) mixtures are designed and specified (e.g. McLaughlin and Goetz 1955, Liebenberg et al. 2004) to avoid moisture damage (e.g. Chen et al. 2004) which is detrimental to pavement performance (e.g. Abdullah et al. 1998, Mohammed et al. 2003). A recent review on the permeability of asphalt concrete (focussing on empirical prediction models) has been published (Vardanega 2014). The hydraulic conductivity of fine-grained materials has been reviewed in many publications (e.g. Olsen 1960, Olson & Daniel 1981). Fine-grained materials may constitute the natural materials that are used as road subgrades.

Comparisons of laboratory and field permeability measurements on AC have been made (e.g. Gogula et al. 2003). Methods for measuring permeability in field conditions have been developed by various researchers using water as a permeant (e.g. Zube 1962, Gerke 1982, Cooley 1999, Fwa et al. 2001) and air as a permeant (e.g. Kari & Santucci 1963). Construction issues such as lift thickness and time for compaction have also been investigated (e.g. Hainin et al. 2013). Neural network approaches for interpreting databases of AC permeability have been published (Tarefder et al. 2005).

1.2 Influence of porosity

A key predictor of asphalt concrete permeability is percentage air voids in the mixture (e.g. Zube 1962, Mullen 1967, Vivar & Haddock 2007, Vardanega 2014). Strictly speaking, the percentage of connected (accessible) voids should be evaluated during testing (cf. Bear 1972). This is not always done in practice but can be done using the ‘hand-pumping’ method (see Smith & Gotolski 1969, p.24 - the method was also used by Kumar & Goetz 1977).

1.3 Study aims

This paper presents the analysis of two databases. Database I (soil) contains over 100 measurements of the hydraulic conductivity of fine-grained soils. Database II (AC) contains over 1300 measurements of the hydraulic conductivity of asphalt concrete. Statistical analysis is performed with both databases using power-law functions. The results are compared to a previously published empirical model for the prediction of asphalt concrete permeability (Vardanega & Waters 2011, 2015).

The nominal maximum aggregate size (NMAS) has been suggested as a key influence on the hydraulic conductivity of asphalt concrete (e.g. Cooley et al. 2002, Yan et al. 2016). Therefore, the effect of NMAS will also be studied using Database II (AC).

2 DATABASE I (SOIL)

2.1 Permeability models

Permeability testing usually employs falling head or constant head approaches (e.g. Bear 1972). Dołżyk and Chmielewska (2014) recently reviewed various empirical and semi-empirical approaches to describe permeability data, emphasizing amongst other factors the importance of the temperature of the permeant – which is not always reported in the literature.

Carrier (2003) recommended that formulations based on the work of Hazen (Hazen 1892, 1911) for modelling permeability should not be used in geotechnical practice (the formulation is shown as equation 1 using the notation of Carrier 2003):

$$k = (C_H)(D_{10})^2 \quad (1)$$

where k is the coefficient of permeability (expressed in units of length per unit time); C_H is an empirical coefficient and D_{10} is the sieve aperture through which exactly ten percent of the material would pass. Carrier (2003) recommended that the Kozeny-Carman formulation (Kozeny 1927, Carman 1938, 1956) should be preferred for use in practice (the formulation is shown as equation 2 using the notation of Carrier 2003):

$$k = (\gamma / \mu)(1 / C_{K-C})(1 / S_o^2)[e^3 / (1+e)] \quad (2)$$

where γ is the unit weight of the permeant (usually water), μ is the dynamic viscosity of the permeating fluid, C_{K-C} is an empirical coefficient, S_o the specific surface area of the soil per unit volume of particles, and e is the void ratio, hereafter denoted as (e_{soil}).

Equation 2 relies on the principles of viscous fluid flow from the Navier-Stokes equation to treat the assembly of soil particles as creating a series of capillary tubes through which a fluid travels (Chapuis & Aubertin 2003). Through this method, it can be shown that the coefficient of permeability (k) strongly varies with the void ratio (e_{soil}). Chapuis & Aubertin (2003) showed that for plastic soils that are “hydrated, saturated, and consolidated before permeability testing”, the Kozeny-Carman formula may be used. Masad et al. (2004, 2006) presented semi-empirical approaches based in part on the Kozeny-Carman formulation to predict the permeability of asphalt concrete using databases.

2.2 Statistical Analysis

Table 1 summarises the sources of the data in Database I (soil). Permeability test data from six publications (ten soils) was collated and statistically analysed. The Matagami Clay and the Louisville Clay were reported as being tested using the constant head approach whereas for the other clays falling head testing was reported. The relationship between

the coefficient of permeability (k) and the Kozeny-Carman void ratio function [$e_{soil}^3/(1+e_{soil})$] is plotted in Figure 1. The coefficient of determination (R^2) of the regression function is 0.564, based on 119 data points (i.e. $n = 119$). The scatter could probably be further reduced if the other parameters in equation (2) were known (cf. Chapuis & Aubertin 2003). The standard error (SE) of the regression is 0.940. The p -value of the regression is < 0.0001 . The RD value for the regression shown in Figure 1 is 66.0%. The relative deviation (RD) is defined in Waters & Vardanega (2009) as:

$$RD = 100 (1-R^2)^{0.5} \quad (3).$$

Figure 2 shows the data re-plotted with $\ln(k)$ predicted using $\ln(e_{soil})$. The resulting trend-lines (re-arranged into power functions) are shown in the figure. The exponent on e_{soil} varies from 1.53 to 5.32 for each of the ten test series analysed. The RD values for the analysis of the individual test series varies from 4.5% ($R^2 = 0.998$) to 55.5% ($R^2 = 0.692$). The exponent on e_{soil} for the whole dataset is 3.29. For the regression of the entire dataset, $R^2 = 0.573$, $RD = 65.4\%$ and $n = 119$. If the possible outlier test series (No. 3) is excluded from the main regression the R^2 increases to 0.624 ($RD = 61.3\%$, $n = 113$).

Table 1. Summary of Database I (soil)

No.	Source	Symbol	Soil Type
①	Al-Tabbaa & Wood (1987)	□	Kaolin
②	Chung et al. (2002)	◇	Pusan Clay
③	Lehka et al. (2003)	○	IIT Clay
④	Lehka et al. (2003)	△	Calcium Bentonite
⑤	Leroueil et al. (1990)*	×	Backebol Clay
⑥	Leroueil et al. (1990)*	■	Matagami Clay
⑦	Leroueil et al. (1990)*	◆	St. Esprit Clay
⑧	Leroueil et al. (1990)*	▲	Louisville Clay
⑨	Pane et al. (1983)	●	Kaolin
⑩	Walker & Raymond (1968)	*	Leda Clay

* Vertical permeability data included in the database




Figure 1. The relationship between k and the Kozeny-Carman void ratio function.




Figure 2. The relationship between $\ln(k)$ and $\ln(e_{soil})$ for the soils in Database I (soil).

3 DATABASE II (AC)

3.1 Original database

Waters (1998) used the D_{50} i.e. the sieve aperture through which 50% of the granular material in the mix would pass in conjunction with the percentage air voids, to define the normalised voids (NV) as $(NV) = [AV(\%)] [D_{50}(\text{mm})] / 4.75$. Vardanega & Waters (2011, 2015) assembled a laboratory database and after performing regression analysis proposed equation (4):

$$k = 0.46(R_p)^{3.70} \quad [R^2 = 0.74; n = 467] \quad (4)$$

where k has units of mm/s and R_p has units of mm and where R_p is the representative pore size (RPS), where, $R_p = (2/3)[AV(\%)/100][D_{75}(\text{mm})]$.

Vardanega & Waters (2011, 2015) selected the effective particle size statistically and determined that the D_{75} (i.e. the sieve aperture through which 75% of the granular material in the mix would pass) was the best fit to the entire dataset (although any effective particle size upwards of D_{50} i.e. the 'coarse fraction', was shown to yield a good fit to the data). Both the normalized voids and the representative pore size concept are based on channel theory work detailed in Taylor's classic textbook (e.g. Taylor 1965,

p.109-110). A more extensive discussion of the derivation of these parameters is given in Waters (1998) and Vardanega & Waters (2011, 2015).

Goode & Lufsey (1965) observed that "Air permeability is a function of aggregate gradation as well as air voids. The effect of gradation was found to be much more pronounced at high air voids than at low air voids". Zhang et al. (2014) used the representative pore size to study pavement permeability and skid resistance; reporting that permeability increases with increasing representative pore size (based on numerical simulations). Waters (1998) compared the normalised voids parameter (NV) with asphalt concrete texture depth and showed that a positive correlation existed (i.e. as NV increased so did the texture depth).

3.2 Expanded database

In this paper, the database of Vardanega & Waters (2011, 2015) has been expanded with data from an additional ten publications. This has increased the number of permeability measurements available for regression analysis to over 1300. The first ten entries in Table 2 are the newly added data sources in this paper.

Table 2. Summary of Database II (AC)

Reference	NMAS (mm) (*)	n^{**}	Stated AV measurement method	Stated k measurement method	R^2 of regression $\ln(k)$ vs. $\ln(Rp, D_{eff}=D_x)^{***}$						
					$\ln(AV)$	$\ln(Rp, D_{10})$	$\ln(Rp, D_{25})$	$\ln(Rp, D_{50})$	$\ln(Rp, D_{75})$	$\ln(Rp, D_{90})$	Best fit
Choubane et al. (1997, 1998)	9.5(1), 12.5(85), 19(65)	151	FM 1-T 166(4) & FM1-T 209(5)	Falling head	0.508	-	0.432	0.536	0.499	0.494	D_{50}
Al-Omari et al. (2002)	12.5(8), 19(2), 25(3)	13	ASSHTO T-166 & Core-lok	Karol-Warner permeameter	0.916	-	0.382	0.588	0.457	0.455	AV
Bhattacharjee & Mallick (2002)	9.5(25), 12.5(45), 19(18)	88	Vacuum seal & Saturated Surface Dry	Falling head	0.632	0.751	0.728	0.678	0.706	0.693	D_{10}
Brown et al. (2004 a,b,c,d)	9.5(131), 12.5(209), 19(64)	404	Vacuum seal & ASSHTO T-166	ASTM PS 129-01; NCAT Field Permeameter	0.532	0.341	0.375	0.421	0.365	0.342	AV
Haddock & Prather (2004)	9.5(5)	5		FDOT method				0.384			
Chen et al. (2004)	19(42)	42	AASHTO T269	Falling head	0.786	0.385	0.963	0.940	0.917	0.893	D_{25}
Norambuena-Contreras et al. (2013) & Norambuena-Contreras (2014)	11.2(18), 16(54)	72	geometric	BS 1377-6	0.845	0.812	0.831	0.846	0.846	0.832	D_{75}
Schmitt et al. (2007)	12.5(19)	19		Falling head test with NCAT device	0.072	0.001	0.018	0.021	0.003	0.027	AV
Pease et al. (2010)	12.5(6)	6		ASTM D5084	0.379	0.736	0.518	0.424	0.650	0.487	D_{10}
Yan et al. (2016)	9.5(12), 12.5(13), 19(7), 25(6), 37.5(13)	51		Falling head (FDOT)	0.519	0.646	0.534	0.591	0.647	0.642	D_{75}
Previous database (Vardanega & Waters 2011, 2015)											
Hewitt (1991)	10(27)	27		Falling head	0.800	0.865	0.879	0.923	0.911	0.921	D_{50}
Maupin (2000, 2009)	9.5(38), 12.5(151)	189		VDOT TM120	0.606	0.362	0.325	0.463	0.557	0.514	AV
Cooley Jr. et al. (2001)	9.5(30), 12.5(45), 19(20), 25(35)	130		Field permeameter	0.430	0.410	0.564	0.683	0.735	0.762	D_{90}
Kanitpong et al. (2001)	12.5(19)	19		ASTM D5084	0.913	0.724	0.679	0.678	0.791	0.877	AV
Mallick et al. (2003)	9.5(20), 12.5(10), 19(9), 25(10)	49		Falling head	0.413	0.620	0.606	0.789	0.807	0.875	D_{90}
Vardanega et al. (2008)	14(53)	53		Falling head	0.380	0.702	0.687	0.722	0.682	0.630	D_{50}
ALL		$n=1318$			0.516	-	0.444	0.554	0.548	0.517	D_{50}

* Number of samples at this NMAS;

** Number of measurements where both a k value and AV value are given (tests where k or AV reported as zero were excluded from the regression analyses);*** Values in bold indicate the highest R^2 for the data sub-set.

In those publications where percentage air voids (AV) were measured using a ‘vacuum method’ in addition to other methods the ‘vacuum’ data was entered into the database. When the NMAS was not stated in the original reference, it was assigned based on the supplied gradation curve.

Table 2 shows the R^2 of the regression of $\ln(k)$ with $\ln(AV)$ and $\ln(R_p)$ with the D_{eff} being assigned as D_{10} , D_{25} , D_{50} , D_{75} and D_{90} . For seven sub-datasets the D_{eff} is not required statistically or weakens the regression (this may be because the range of gradations in the sub-dataset is not significant) but for nine of the sub-datasets improvement is shown.

Analysis of the entire data-set ($n = 1318$) shows that D_{50} is actually the preferred choice for the effective particle size. The D_{50} was used by Waters (1998) when developing the ‘normalised voids’ approach. Statistically, the D_{75} remains an acceptable choice for D_{eff} (the R^2 is similar to that of D_{50} for the whole dataset). In order to compare the analysis of the updated database with the regression relationships reported in Vardanega & Waters (2011, 2015) the D_{75} will be used to compute the RPS in the analysis that follows in this paper.

Figure 3 shows that $\ln(AV)$ is a key predictor of $\ln(k)$ (as is void ratio for fine-grained soils, see Figure 2). Figure 4 shows that the inclusion of the effective particle size via the R_p parameter does slightly increase the R^2 (and visually reduce some of the scatter) but the effect is not as marked as that reported in Vardanega & Waters (2011, 2015). The updated trend-line is given as equation (5):

$$\ln(k) = 3.578 \ln(R_p) - 1.645 \quad (5)$$

$[R^2 = 0.548; n = 1318; SE = 1.581; RD = 67.2\%]$

where k has units of mm/s and R_p has units of mm. Equation (5) can be re-arranged to give:

$$k = 0.193(R_p)^{3.58} \quad (5a).$$




Figure 3. $\ln(k)$ versus $\ln(AV)$ for the expanded database (air voids expressed numerically not as a percentage).

3.3 Influence of NMAS

The NMAS may affect the co-efficient of permeability as recently reported by Yan et al. (2016). NMAS is not explicitly accounted for in equation 5. Figures 5 and 6 show the database subdivided into mixtures that have $NMAS \leq 12.5\text{mm}$ (Figure 5) and those with $NMAS > 12.5\text{mm}$ (Figure 6).




Figure 4. $\ln(k)$ versus $\ln(R_p)$ for the expanded database (D_{75} was used as the effective particle size).

3.3.1 $NMAS \leq 12.5\text{mm}$

Figure 5 shows (as with Figure 4) that the fitted trend-line is similar to that proposed in Vardanega & Waters (2011, 2015). Therefore, for mixtures with $NMAS \leq 12.5\text{mm}$ we can write:

$$\ln(k) = 3.668 \ln(R_p) - 1.313 \quad (6)$$

$[R^2 = 0.603; n = 917; SE = 1.351; RD = 63.0\%]$

where k has units of mm/s and R_p has units of mm. Equation (6) can be re-arranged to give:

$$k = 0.269(R_p)^{3.67} \quad (6a).$$

For this sub-dataset ($NMAS \leq 12.5\text{mm}$) the R^2 value when $\ln(k)$ is regressed against $\ln(AV)$ is 0.555.

3.3.2 $NMAS > 12.5\text{mm}$

Figure 6 shows (as with Figure 4) that the fitted trend-line is similar to that proposed in Vardanega & Waters (2011, 2015). Therefore, for mixtures with $NMAS > 12.5\text{mm}$ we can write:

$$\ln(k) = 4.123 \ln(R_p) - 1.872 \quad (7)$$

$$[R^2 = 0.540; n = 401; SE = 1.875; RD = 67.8\%]$$

where k has units of mm/s and R_p has units of mm. Equation (7) can be re-arranged to give:

$$k = 0.154(R_p)^{4.12} \quad (7a).$$

For this sub-dataset ($NMAS > 12.5\text{mm}$) the R^2 value when $\ln(k)$ is regressed against $\ln(AV)$ is 0.470.

Figure 7 shows equations (4, 5a, 6a and 7a) compared. Bearing in mind the degree of scatter in the data shown in Figures 5 and 6 there is not a significant difference between the two sub-sets in the database (NMAS > 12.5mm and NMAS ≤ 12.5mm), however for smaller datasets with consistent testing methods the effect may be more visible (cf. Yan et al. 2016).




Figure 5. $\ln(k)$ versus $\ln(R_p)$ for the mixtures in the database with NMAS ≤ 12.5 mm.




Figure 6. $\ln(k)$ versus $\ln(R_p)$ for the mixtures in the database with NMAS > 12.5 mm.




Figure 7. Comparison of regression equations derived from the database analysis.

4 DISCUSSION

The results of the analysis of Database II (AC) reveal that while the representative pore size (R_p) remains a useful parameter to predict the coefficient of permeability, there are limitations - including:

- (i) use of power laws means that coefficient of permeability values reported as ‘zero’ cannot be included (even if some air voids are reported) in the database;
- (ii) some of the scatter on Figure 4 is probably due to the mixing and matching of various air void measurement methods being present in the database (connected voids are not always explicitly measured in practice).

Therefore, further work studying the influence of the ‘shape of the grading curve’ on asphalt concrete permeability is proposed. Some preliminary work using ‘grading entropy’ (e.g. Lőrincz 2005) has recently been undertaken (James 2015) as part of this on-going study.

5 SUMMARY

This paper has presented the results of the analysis of two databases of hydraulic conductivity measurements on road building materials. The analysis of Database I (soil) revealed that the exponent on void ratio varies and on average is about 3.3. Database II (AC) was used to show that the original empirical equation presented in Vardanega & Waters (2011, 2015) is similar to that generated using the expanded database presented in this paper. The revised exponent on the R_p parameter was computed to be around 3.6. However, the influence of the grading parameter on reducing the scatter about the regression line is not as marked as reported in Vardanega & Waters (2011, 2015). The effect of NMAS was statistically detectable but relatively minor compared to the influence of air voids.

6 ACKNOWLEDGMENTS

CJS undertook some of this work with the support of a University Research Committee Interdisciplinary Research Internship in 2015 at the University of Bristol. SF thanks Dr Erdin Ibrahim for co-supervising her MSc project. PJV thanks Mr Max James for his helpful comments.

7 REFERENCES

Abdullah, W.S., Obaidat, M.T. and Abu-Sa’da, N.M. 1998. Influence of Aggregate Type and Gradation on Voids of Asphalt Concrete Pavements. *Journal of Materials in Civil Engineering*, 10(2): 76-85.

- Al-Omari, A., Tashman, L., Masad, E., Cooley, A. and Harman, T. 2002. Proposed Methodology for Predicting HMA Permeability. *Journal of Association of Asphalt Paving Technologists* 71: 30-58 (includes discussion).
- Al-Tabbaa, A. and Wood, D.M. 1987. Some measurements of the permeability of kaolin. *Géotechnique* 37(4): 499-503.
- Bear, J. 1972. *Dynamics of fluids in porous media*, American Elsevier Publishing, New York, NY.
- Bhattacharjee, S. and Mallick, R.B. 2002. An Alternative Approach for the Determination of Bulk Specific Gravity and Permeability of Hot Mix Asphalt (HMA). *International Journal of Pavement Engineering*, 3(3): 143-152.
- Brown, E.R., Hainin, M.R., Cooley, A. and Hurley, G. 2004a. Relationships of HMA in-place air voids, lift thickness, and permeability Volume One. *NCHRP web document 68* < http://onlinepubs.trb.org/onlinepubs/nchrp/nchrp_w68v1.pdf > (19 Nov. 2016).
- Brown, E.R., Hainin, M.R., Cooley, A. and Hurley, G. 2004b. Relationships of HMA in-place air voids, lift thickness, and permeability Volume Two. *NCHRP web document 68* < http://onlinepubs.trb.org/onlinepubs/nchrp/nchrp_w68v2.pdf > (19 Nov. 2016).
- Brown, E.R., Hainin, M.R., Cooley, A. and Hurley, G. 2004c. Relationships of HMA in-place air voids, lift thickness, and permeability Volume Three. *NCHRP web document 68* < http://onlinepubs.trb.org/onlinepubs/nchrp/nchrp_w68v3.pdf > (19 Nov. 2016).
- Brown, E.R., Hainin, M.R., Cooley, A. and Hurley, G. 2004d. Relationships of HMA in-place air voids, lift thickness, and permeability Volume Four. *NCHRP web document 68* < http://onlinepubs.trb.org/onlinepubs/nchrp/nchrp_w68v4.pdf > (19 Nov. 2016).
- Carman, P.C. 1938. The determination of the specific surface of powders. I. *Journal of the Society of Chemical Industry (Transactions)*, 57, 225-234.
- Carman, P.C. 1956. *Flow of gases through porous media*, Butterworths Scientific Publications, London.
- Carrier, W.D. 2003. Goodbye, Hazen; Hello, Kozeny-Carman. *Journal of Geotechnical and Geoenvironmental Engineering*, 129(11): 1054-1056.
- Chapuis, R.P. and Aubertin, M. 2003. On the use of the Kozeny-Carman equation to predict the hydraulic conductivity of soils. *Canadian Geotechnical Journal* 40(3): 616-628.
- Chen, J.-S., Lin, K.-Y. and Young, S.-Y. 2004. Effects of Crack Width and Permeability on Moisture-Induced Damage of Pavements. *Journal of Materials in Civil Engineering*, 16(3): 276-282.
- Choubane, B., Page, G.C. and Musselman, J.A. 1997. Investigation of Water Permeability of Coarse Graded Superpave Pavements. *Research Report FL/DOT/SMO/97-416*, Department of Transportation, FL.
- Choubane, B., Page, G.C. and Musselman, J.A. 1998. Investigation of Water Permeability of Coarse Graded Superpave Pavements. *Journal of Association of Asphalt Paving Technologists* 67: 254-276 (includes discussion).
- Chung, S.G., Giao, P.H., Kim, G.J. and Leroueil, S. 2002. Geotechnical properties of Pusan clays. *Canadian Geotechnical Journal*, 39(5): 1050-1060.
- Cooley, L.A., Jr. 1999. Permeability of Superpave Mixtures: Evaluation of field permeameters. *Report no. 99-01*, National Centre for Asphalt Technology, Auburn University, Auburn, Ala.
- Cooley, L.A., Jr., Brown, E.R. and Maghsodloo, S. 2001. Development of Critical Field Permeability and Pavement Density Values for Coarse Graded Superpave Pavements. *Report no. 01-03*, National Centre for Asphalt Technology, Auburn University, Auburn, Ala.
- Cooley, L.A., Jr., Prowell, B.D. and Brown, E.R. 2002. Issues Pertaining to the Permeability Characteristics of Coarse Graded Superpave Mixes. *Journal of Association of Asphalt Paving Technologists* 71: 1-29 (includes discussion).
- Dołżyk, K. and Chmielewska, I. 2014. Predicting the coefficient of permeability of non-plastic soils. *Soil Mechanics and Foundation Engineering* 51(5): 213-218.
- Fwa, T.F., Tan, S.A., Chuai, C.T. and Guwe, Y.K. 2001. Expedient Permeability Measurement for Porous Pavement Surface. *International Journal of Pavement Engineering*, 2(4): 259-270.
- Gerke, R.J. 1982. In situ testing infiltration of water through road pavements. In *Proceedings 11th Australian Road Research Board Conference. Part 2*. Australian Road Research Board, Melbourne, VIC, pp. 178-192.
- Gogula, A., Hossain, M., Romanoschi, S. and Fager, G.A. 2003. Correlation between Laboratory and Field Permeability Values for the Superpave Pavements. In *Proceedings of the 2003 Mid-Continent Transportation Research Symposium, Ames, Iowa, August 2003*. < <http://www.ctre.iastate.edu/pubs/midcon2003/gogulasuperpave.pdf> > (19 Nov. 2016).
- Goode, J.F. and Lufsey, L.A. 1965. Voids permeability, film thickness vs. asphalt hardening. *Journal of Association of Asphalt Paving Technologists* 34: 430-463 (includes discussion).
- Haddock, J.E. and Prather, M. 2004. Investigation of permeability on Indiana SR-38. *Journal of Performance of Construction Facilities*, 18(3): 136-141.
- Hainin, M.R., Yusoff, N.I.Md., Satar, M.K.I.M.S. and Brown, E.R. 2013. The effect of lift thickness on permeability and the time available for compaction of hot mix asphalt pavement under tropical climate condition. *Construction and Building Materials*, 48: 315-324.
- Hazen, A. 1892. Some physical properties of sands and gravels, with special reference to their use in filtration. *24th Annual Report Pub. Doc. 34*. Massachusetts State Board of Health, Boston, pp. 539-556.
- Hazen, A. 1911. Discussion of 'Dams on sand foundations' by A.C. Koenig. *Transactions American Society of Civil Engineers* 73: 199-203.
- Hewitt, C. 1991. *A study of asphalt permeability*. BE thesis, University of Central Queensland, Rockhampton, Qld.
- James, M.A. 2015. *The Grading Entropy and Permeability of Road Surfaces*. Undergraduate research project report (unpublished), University of Bristol, Bristol, UK.
- Kanitpong, K., Benson, C.H. and Bahia, H.U. 2001. Hydraulic conductivity (permeability) of laboratory-compacted asphalt mixtures. *Transportation Research Record 1767*, Paper No. 01-2997, Transportation Research Board, Washington, DC, 25-32.
- Kari, W.J. and Santucci, L.E. 1963. Control of Asphalt Concrete Construction by the Air Permeability Test. *Journal of the Association of Asphalt Paving Technologists*, 32: 148-170 (includes discussion).
- Kozeny, J. 1927. Über kapillare Leitung des Wassers in Boden. *Wien. Akad. Wiss.* 136(2a): 271-306. (in German).
- Kumar, A. and Goetz, W.H. 1977. Asphalt Hardening as Affected by Film Thickness, Voids and Permeability in Asphaltic Mixtures. *Journal of Association of Asphalt Paving Technologists* 46: 571-605 (includes discussion).
- Lekha, K.R., Krishnaswamy, N.R. and Basak, P. 2003. Consolidation of Clays for Variable Permeability and Compressibility. *Journal of Geotechnical and Geoenvironmental Engineering*, 129(11): 1001-1009.
- Leroueil, S., Bouclin, G., Tavenas, F., Bergeron, L. and LaRochelle, P. 1990. Permeability anisotropy of natural clays as a function of strain. *Canadian Geotechnical Journal*, 27(5): 568-579.
- Liebenberg, J.J.E., Rossmann, D. and Fletcher, C. 2004. Asphalt Mix Design and Construction: A Selection of Possible Pitfalls. In *Proceedings 8th Conference on Asphalt Pave-*

- ments for Southern Africa (CAPSA '04) 12-16 September 2004, Sun City, South Africa, Paper No. 035.
- Lőrincz, J., Imre, E., Gálos, M., Trang, Q.P., Rajkai, K., Fityus, S. and Telekes, G. 2005. Grading Entropy Variation Due to Soil Crushing. *International Journal of Geomechanics*, 5(4): 311-319.
- Mallick, R.E., Cooley, L.A., Jr., Teto, M.R., Bradbury, R.L. and Peabody, D. 2003. An Evaluation of Factors Affecting Permeability of Superpave Designed Pavements. *Report no. 03-02*, National Centre for Asphalt Technology, Auburn University, Auburn, Ala.
- Masad, E., Al-Omari, A. and Lytton, R. 2006. Simple Method for Predicting Laboratory and Field Permeability of Hot-Mix Asphalt. *Transportation Research Record 1970*, Transportation Research Board, Washington, DC, pp. 55-63.
- Masad, E., Birgisson, B. and Al-Omari, A. 2004. Analytical Derivation of Permeability and Numerical Simulation of Fluid Flow in Hot Mix Asphalt. *Journal of Materials in Civil Engineering*, 16(5): 487-496.
- Maupin, G.W. Jr. 2000. Asphalt permeability testing in Virginia. *Transportation Research Record 1723*, Paper No. 00-1206, Transportation Research Board, Washington, DC, pp. 83-91.
- Maupin, G.W. Jr. 2009. *Personal Communication*.
- McLaughlin, J.F. and Goetz, W.H. 1955. Permeability, Void Content, and Durability of Bituminous Concrete. *Highway Research Board Proceedings*, 34: 274-286.
- Mohammad, L.N., Herath, A. and Huang, H. 2003. Evaluation of Permeability of Superpave® Asphalt Mixtures. *Transportation Research Record 1723*, Paper No. 03-4464, Transportation Research Board, Washington, DC, pp. 50-58.
- Mullen, W.G. 1967. Beam flexure and permeability testing of bituminous pavement samples. *Journal of the Association of Asphalt Paving Technologists* 36: 615-631.
- Norambuena-Contreras, J. 2014. *Personal Communication*.
- Norambuena-Contreras, J., Izquierdo, E.A., Castro-Fresno, D., Partl, M.N. and Garcia, Á. 2013. A New Model on the Hydraulic Conductivity of Asphalt Mixtures. *International Journal of Pavement Research and Technology*, 6(5): 488-495.
- Olsen, H.W. 1960. Hydraulic Flow Through Saturated Clays. *Clays and Clay Minerals* 9(1): 131-161.
- Olson, R.E. and Daniel, D.E. 1981. Measurement of the Hydraulic Conductivity of Fine-Grained Soils. In Zimmie, T.F. and Riggs, C.O. (Eds.) *Permeability and Groundwater Contaminant Transport ASTM STP 746*, American Society for Testing and Materials, West Conshohocken, PA, pp. 18-64.
- Pane, V., Croce, P., Znidarcic, D., Ko, H.-Y., Olsen, H.W. and Schiffman, R.L. 1983. Effects of consolidation on permeability measurements for soft clay. *Géotechnique*, 33(1): 67-72.
- Pease, R.E., Stormont, J.C., Hines, J. and O'Dowd, D. 2010. Hydraulic Properties of Asphalt Concrete. *Geotechnical Testing Journal*, 33(6): 445-452.
- Schmitt, R.L., Owusu-Ababio, S., Crovetti, J.A. and Cooley, A.L., 2007. Development of In-Place Permeability Criteria for HMA Pavement in Wisconsin (No. WHRP 06-15). <<http://minds.wisconsin.edu/bitstream/handle/1793/53421/06-02%2520Final%2520Report.pdf>> (22 Feb. 2017)
- Smith, R.W. and Gotolski, W.H. 1969. A study of physical factors affecting the durability of asphaltic pavements. PB 189 832, Pennsylvania State University, University Park, PA.
- Tarefder, R.A., White, L. and Zaman, M. 2005. Neural Network Model for Asphalt Concrete Permeability. *Journal of Materials in Civil Engineering*, 17(1): 19-27.
- Taylor, D.W. 1965. *Fundamentals of Soil Mechanics*, John Wiley & Sons Inc, New York, NY.
- Vardanega, P.J. 2014. State of the Art: Permeability of Asphalt Concrete. *Journal of Materials in Civil Engineering* 26(1): 54-64.
- Vardanega, P.J., Natatmadja, A., Waters, T. and Ramanujam, J. 2008. A study of asphalt permeability: Empirical permeability models. In *Proceedings of the 23rd ARRB Conference – Research Partnering with Practitioners* (CD-ROM), ARRB Group, Melbourne, VIC.
- Vardanega, P. J. and Waters, T. J. 2011. Analysis of Asphalt Concrete Permeability Data Using Representative Pore Size. *Journal of Materials in Civil Engineering* 23(2): 169-176.
- Vardanega, P.J. and Waters, T.J. 2015. Erratum for “Analysis of Asphalt Concrete Permeability Data Using Representative Pore Size” by P. J. Vardanega and T. J. Waters. *Journal of Materials in Civil Engineering*, 27(8): 08215002.
- Vivar, E. and Haddock, J.E. 2007. Hot-mix asphalt permeability and porosity. *Journal of the Association of Asphalt Paving Technologists* 76: 953-979.
- Walker, L.K. and Raymond, G.P. 1968. The prediction of consolidation rates in a cemented clay. *Canadian Geotechnical Journal*, 5(4): 192-216.
- Waters, T. J. 1998. A study of water infiltration through asphalt road surface materials. In *Proceedings of the International Symposium on Subdrainage in Roadway Pavements and Subgrades*. Asociación Técnica de Carreteras, Madrid, Spain, 311-317.
- Waters, T.J. and Vardanega, P.J. 2009. Re-examination of the coefficient of determination (r^2) using road materials engineering case studies. *Road and Transport Research* 18(3): 3-11.
- Yan, Y., Zaniewski, J.P., Hernando, D. 2016. Development of a predictive model to estimate permeability of dense-graded asphalt mixture based on volumetrics. *Construction and Building Materials* 126: 426-433.
- Zhang, L., Ong, G.P. and Fwa, T.F. 2014. Influences of Pore Size on the Permeability and Skid Resistance of Porous Pavement. *3rd International Conference on Transportation Infrastructure, ICTI 22-25 April 2014*, Pisa, Italy. pp. 621-632.
- Zube, E. 1962. Compaction of asphalt concrete pavement as related to the water permeability test. In: *Proceedings 41st Annual Meeting Highway Research Board*, Washington DC, pp. 12-37.